

# Functionalization of Amberlite XAD-4 with 8-hydroxyquinoline chelator using aryldiazonium radical reaction and its application for solid phase extraction of trace metals from groundwater samples

Hind N. AlHarbi and Awadh O AlSuhaimi\*

Chemistry Department, Faculty of Science, Taibah University, Prince Nayef Road, P.O. Box 344, AlMedianh AlMunawarah 42353, Saudi Arabia

## ABSTRACT


In this work, the aryldiazonium salts radical addition method has been used successfully to anchor 8-hydroxyquinoline (8-HQ) moieties onto the surface of Amberlite XAD-4 beads. The nitroaniline aryldiazonium salt was generated (in-situ) and covalently grafted onto Amberlite XAD-4 by aid of hypophosphorous acid as a catalyst to facilitate the anchorage of 8-HQ chelator making use of the conventional diazo coupling. The successfulness of the synthesized chelating resin was confirmed by (ATR-IR), (TGA) and (XPS). The resin was packed into cartridges and used with standard solid phase extraction (SPE) apparatus for the extraction of trace metals; Co (II), Ni (II) and Cu (II) from groundwater samples prior to their measurement by (ICP-MS). The resin exhibited more than 90% enhancement in capacity exchange relative to the plain Amberlite XAD-4. Under the optimum conditions the sorption capacity of the sorbent was 0.366, 0.265 and 0.328 (mM/g) for Co (II), Ni (II) and Cu (II) respectively. The sorbent showed efficient performance when applied for SPE of trace metals from groundwater real samples from AlMadinah AlMumnawarah, Saudi Arabia.

**Keywords:** Solid phase extraction, Amberlite XAD-4, Chelating Resin, Trace metals, ICP-MS, and Groundwater.

---

\* Corresponding author [asuhaimi@taiabhu.edu.sa](mailto:asuhaimi@taiabhu.edu.sa)

Graphical Abstract



ACCEPTED MANUSCRIPT

## 1. Introduction

Heavy metals (HMs) are categorized as extremely toxic environmental pollutants (Srivastava & Goyal, 2010). They occur as natural constituents of earth crust, but many anthropogenic process accompanying the steadily growth of urbanization activities have increased the amount of heavy metals deposited onto earth surface several times greater than the background level from natural sources (Khan et al., 2011). HMs possess crucial hazardous effects to biota, animal, and human being because of their toxicity, bio-accumulative and non-biodegradable nature (Lichtfouse et al., 2013; Bazrafshan et al., 2015). Frequently, HMs exist within very complex matrices at sufficiently low levels. Therefore, their accurate quantification is a challenging analytical task (Brown & Milton, 2005).

The truthful determination of trace analytes in distinct sample matrices is always a central objective for any analytical procedure, however, most of the available analytical techniques do not enable direct analysis. Therefore, an appropriate sample pretreatment step is usually required to separate the analytes from the matrix and preconcentrate them before their determination (Hu & He, 2012 ; Liu et al., 2007 ; Wang et al., 2003).

There are many procedures based on various separation concepts to enrich trace elements from accompanying interferences. The choice of the suitable method depends on certain distinctive parameters including sample nature, concentrations of the analytes and the analytical techniques to be used in final measurement determine the adequate sample preparation method ( Liu et al., 2004). Examples of the common separation/extraction methods are; coprecipitation (Mendil et al., 2015), ion exchange (Dabrowski et al., 2004), electro-deposition (Armstrong et al., 1996) , cloud point extraction (Shemirani & Yousefi, 2007), membrane filtration (Soylak et al., 2007),

solid phase extraction (SPE) (sometimes referred to as liquid–solid extraction) (Nickerson, 2011), adsorption (Liu et al., 2007) and liquid–liquid extraction (LLE) (Korn et al., 2006).

Among the numerous extraction and enrichment methods, SPE has become one of the most efficient multielement pre-concentration process for wide range of organic and inorganic analytes (Dabrowski, 1998; Huck & Bonn, 2000). Perhaps because SPE offers many advantages such as high recovery, short extraction time, low cost, simplicity and low consumption (or none) of organic solvents (Golshaei et al., 2015; Liu et al., 2007).

The ever continues research efforts in SPE provided science community with wide variety of (selective) SPE materials. Regularly, these materials prepared either by physical modifications (impregnation) or chemical modifications (chemical binding of selected moieties e.g., chelating agents for metals) to various solid supports, such as activated carbon, alumina, cellulose, silica gel, polyacrylate polymer and XAD resins, are useful substrates for the synthesis of SPE materials (Zhai et al., 2010)

The commercially available Amberlite resins are very promising substrate for the design of chelating matrices due to their characteristic physical and chemical properties such as high surface area, porosity, purity and durability (Ahmad et al., 2015). The well-known member of Amberlite XAD series; Amberlite XAD-4 which is a porous cross-linked polystyrene divinylbenzene polymer, has found immense applications for the enrichment/separation of trace metals ions (Uzun et al., 2001). Amberlite XAD resins have attracted much attention of researchers in the last few years for their appropriateness to be functionalized with broad range of specific chelating moieties.

The chelated resins showed good performance as solid phase extractants (SPE) for preconcentration metal ions from various matrices in various applications ( Gao et al., 2010). Noticeably, most of the published chemical modification methods were based on the nitration step of phenyl ring with sulfuric and nitric acids followed by a diazo-coupling reaction (Jung et al., 2010; Saxena &Meena, 2014).

The recently introduced chemical modification that uses the radical addition of aryldiazonium salts in presence of hypophosphorous acid as catalyst, is a very convenient approach for the addition of reactive functional group to the surface of carbon and other substrates. The obtained intermediate from radical addition reaction is amenable for the attachment of many moieties utilizing various chemical transformations like azo coupling scheme (Pandurangappa and Raghu, 2011).

Oxin chelating agents are very useful in analytical chemistry and radiochemistry applications, mainly for the extraction and fluorometric spectrophotometric determination of metal ions (Kosa et al., 2012). 8-Hydroxyquinoline (8-HQ) is the most popular oxin chelators due to its capability to form stable complexes with many metal ions. 8-HQ and its derivatives are among the early chelating moieties that being successfully employed in the synthesis of chelating resins, due to their preferable chelating capacity for wide range of transition and heavy metals over alkaline earth cations (Wegscheider & Knapp, 1981).

A previous work in our laboratory showed that the chemical reduction of aryldiazonium salts method was a reliable approach for the covalent attachment of 8-HQ onto activated carbon (Alqadhi and Alsuhami, 2020). In this work, the method was proposed as green chemistry process for the chemical attachment of 8-HQ chelator onto amberlite XAD-4 substrate. The performance of synthesized metal chelator as

SPE materials for sample preparation of trace metals from groundwater samples has been optimized.

## 2. Experimental Work

### 2.1. Chemical Reagents

All chemicals used in this work were of analytical reagent-grade and all working solutions were prepared in Millipore water ( $\leq 18.2 \Omega$ ). The solid support Amberlite XAD-4 (polystyrene divinylbenzene type, bead size 20-60 mesh and surface area of  $750 \text{ m}^2/\text{g}$ ) were purchased from Sigma-Aldrich chemie GmbH (Darmstadt, Germany). The 4-nitroaniline, sodium hydrosulfite ( $\text{Na}_2\text{S}_2\text{O}_4$ ), 8-Hydroxyquinoline and hypophosphorous acid were obtained from Acros Organics (Geel, Belgium), Sodium Nitrite ( $\text{NaNO}_2$ ) was purchased from Loba Chemie (Mumbai, India). Hydrochloric acid and nitric acid from Panreac Quimica, SA (Barcelona, Spain) and ethanol from Fisher Scientific (Loughborough, UK).

Metals standard solutions were prepared from Elemental stock solutions  $1 \text{ mg/ml}$ , Acros Organics (Geel, Belgium) by proper dilution. Ammonium acetate purchased from Sigma-Aldrich chemie GmbH (Darmstadt, Germany), buffer was prepared from ammonium acetate and purified by passing through a column of Chelex-100 from Bio-Rad (Hercules, CA, USA). The pH was adjusted to the required values with nitric acid, acetic acid from Sigma Aldrich (Darmstadt, Germany) or liquid ammonia from Panreac (Barcelona, Spain). Ultrapure water produced with a Millipore Milli-Q water purification system (Darmstadt, Germany). All the glassware which used in the experiments were soaked overnight into a 5% (v/v) nitric acid solution and rinsed thoroughly with purified water before usage.

## 2.2. Instrumentation and Measurements

ICP-MS 7500 series, Agilent Technologies (Santa Clara, California, USA) was used for the determination of metal ions. The instrument preset at the standard operating parameters recommended by manufacturer. The pH measurements were done using a Basis pH meter HI 2211 pH/ORP meter (HANNA Instrument Company, Carrollton, Texas, USA).

IR spectra were recorded in the range of 400-4000  $\text{cm}^{-1}$  using Thermo NICOLET 380 FTIR equipped with attenuated total reflection (ATR) accessory (Thermo-Fisher Scientific, Waltham, Massachusetts, USA). X-Ray photoelectron spectroscopy (XPS) for C1s, N1s and O1s were performed on CAE: Pass Energy 150.0 eV (Thermo Scientific, Waltham, Massachusetts, USA) equipped with Al K Alpha with a step size of 1 eV. Thermogravimetric analysis (TGA) was carried out under nitrogen atmosphere at a heating rate 10  $\text{C}^{\circ}/\text{min}$  using TA instrument, model SDT Q600, (Tokyo, Japan).

## 2.3. Preparation of 8-HQ-amberlite XAD-4 Chelating Resin

The 8-HQ-amberlite XAD-4 chelating resin was prepared using a simple three- step chemical transformation as shown follows:

Firstly, the 4-nitroaniline diazonium salt radical was generated in situ by dissolving 2g of 4-nitroaniline into 50 ml 1:1 solution of HCl: water. The solution was cooled in ice-bath and a cold solution of 2g  $\text{NaNO}_2$  dissolved in water was added dropwise with continues stirring (Saylam et al., 2014). Then a 20 g of amberlite XAD-4 was added and a 50 ml of hypophosphorous acid ( $\text{H}_3\text{PO}_2$ , 50% V/V in water) solution was added slowly. The solution was stirred at 0-5  $\text{C}^{\circ}$  for 2h. Then, filtered, washed with deionized water to remove any excess acid and finally washed with acetone to clean the product from any residual diazonium salt molecules. The functionalized XAD-4 was

then vacuum dried for 24h before being used in the subsequent stage (Kempegowda & Malingappa, 2013; Abiman et al., 2008; Wildgoose et al., 2005).

In second step nitro groups on the surface of XAD-4 was reduced using 50 ml solution of 5% sodium hydrosulfite ( $\text{Na}_2\text{S}_2\text{O}_4$ ) in a sealed flask at  $45\text{ C}^\circ$  for 24h to insure a maximum conversion of  $(-\text{NO}_2)$  groups into  $(-\text{NH}_2)$  groups. The product was filtered and washed with cold water to remove any excess of salt and used in the diazocoupling step (Scheuerman & Tumelty, 2000; Fan et al., 2007).

In third step, the aminobenzyl-XAD-4 was diazotized for 1.5h at  $0-5\text{ C}^\circ$  with 50 ml of 2% (w/v)  $\text{NaNO}_2$  in 1% acetic acid solution. Then filtered immediately, washed with cold water and a 50 ml of 1% 8-HQ solution in ethanol was added dropwise to the mixture for 4h with frequent mechanical shaking to allow the diazicoupling reaction to complete.

The obtained resin was filtered, washed with ethanol, water, 2% HCl solution and water until the filtrate showed no characteristic color. The chelator was then vacuum dried and stored in desiccator till the subsequent use (Fan et al., 2007).

#### **2.4. Chelator sorption performance**

In order to evaluate the sorption capability of the synthesized metal chelator, it has been used a SPE sorbent for Co, Ni and Cu from standard solutions and groundwater real samples. These metal ions were chosen as a prove of concept.

#### **2.5. Sorption Capacity Study**

The sorption capacity (maximum amount of metal adsorbed per gram) of the prepared chelator; AXAD-4-8HQ was determined for Co, Ni and Cu in batch mode experiment.

This test was performed by placing 0.25 g of dry resin into 50 ml conical flask and 10 ml of 100 mg/L solution of each metal prepared in ammonium acetate buffer (0.2 M, pH 6) was added. The mixture was left to equilibrate overnight over a mechanical shaker. The solution was centrifuged and the amount of the remained metal ions in the supernatant solution were quantified against the original concentration using ICP-MS.

## **2.6. Effect of solution pH**

The optimum pH of metal ion uptake was determined by static batch experiment. Briefly, 0.1 g of the dry chelated AXAD-4-8HQ resin was suspended into 10 ml of multi-elements solutions containing 100 ng/ml of Co, Ni and Cu in 0.2 M ammonium acetate solution. The pH of the metal ions solution was adjusted prior to equilibration over a range (pH 2-10) with nitric acid (0.1 M), acetic acid (0.1M) or ammonia (0.1 M). The solutions were then centrifuged, and the residual metal concentration of the supernatant was measured versus the original concentration using ICP-MS. All experiments were performed in triplicate (AlSuhaimi et al., 2017; Islam et al., 2010).

## **2.7. Effect of contact time**

The potential of this parameter was investigated for the sorption of metal ions; Co, Ni and Cu as a function of time in batch mode experiment. Briefly, the synthesized AXAD-4-8HQ resin (0.1gm) was agitated with 100 ml of solution containing (100 ng/ml) of the tested metal ions and left to equilibrate for different time intervals (2, 5, 10, 15, 30, 45, 60, 80 and 120 min). The concentration of metal ions in the supernatant solution was determined by ICP-MS.

## 2.8. SPE Manifold and procedure

The dynamic SPE experiments conducted using a 12-way standard SPE manifold (Ato Science, China) operated with a vacuum pump (AP-9950; Ato Science, China). About 0.5g of the synthesized resin packed into SPE cartridges (bond straight barrel; Agilent Technologies) to make discs of 5 mm height sandwiched between a pair of porous Teflon filters. The SPE protocol performed according to the following sequences. Initially, the SPE cartridges were conditioned by passing 5 ml of buffer solution at 1 ml/min flow rate and then 25 ml of samples were loaded at 0.5 ml/min flow rate. After that, the cartridges were flushed with 5 ml of water (at 0.5 ml/min) to remove any residual metals and matrices. Finally, the sequestered (chelated) metal ions were eluted with 2.5 ml of 1.5 M HNO<sub>3</sub> at a flow rate of 2 ml/min. The eluted metals were collected into 10 ml PTFE sample tubes and diluted with 5 ml Millipore water for ICP-MS analyses. This protocol has been used for all the standards and the real samples (Zhao et al., 2011; Liu et al., 2014)

### 3. Results and Discussion

#### 3.1. Chemical modification reaction

The attachment of 8-HQ chelating agent onto the surface of Amberlite XAD-4 was attained making use of a three-step chemical reaction as shown schematically in (**Fig.1**). In first step, 4-nitroaniline groups were covalently anchored onto Amberlite XAD-4 surface throughout the chemically activated one-electron reduction of the in-situ generated 4-nitrobenzenediazonium salt intermediate in the presence of hypophosphorous acid as a reducing catalyst. Meanwhile the second step involves the reduction of nitro groups into amines using sodium hydrosulfite ( $\text{Na}_2\text{S}_2\text{O}_4$ ). In the final step, the 8-HQ moiety was coupled onto Amberlite XAD-4 via the classical diazo linkage (Kempegowda & Malingappa, 2013; Abiman et al., 2008; Wildgoose et al., 2005 ; Scheuerman & Tumelty, 2000; Fan et al., 2007).




Fig. 1: reaction sequence of XAD-4 functionalization with 8-HQ

## 3.2. Characterization of AXAD4-8HQ Resin

### 3.2.1. ATR-IR characterization

The successfulness of AXAD4-8HQ resin synthesis has been confirmed by ATR-IR analysis. The IR spectrum of AXAD4-8HQ is compared with that of that of a plain Amberlite XAD-4 (**Fig. 2**). Obviously, few bands in the regions 1560-1345 cm<sup>-1</sup> and 1250-500 cm<sup>-1</sup> which are due to the plain resin, can be seen in both spectra. The linkage of 8-HQ moiety however can be recognized from many IR bands. These include, the appearance of the distinctive band at 3448.98 cm<sup>-1</sup> in IR spectrum of the AXAD4-8HQ

resin which belong to phenolic hydroxyl group (O-H), and the band at  $2927.11\text{ cm}^{-1}$  that comes from C-H (stretching). The existence of C=N connection is clearly identified from the band around  $1604.53\text{ cm}^{-1}$ . The fingerprint peak at  $1345.99\text{ cm}^{-1}$  confirmed the presence of C-N and that observed at  $1560.39\text{ cm}^{-1}$  confirms the existence of -N=N-. This result indicates that the 8-HQ moiety has been successfully immobilized onto Amberlite XAD-4 surface through diazotized N=N coupling (Cheira, 2015; Saxena & Meena, 2014; Nezhati et al., 2010).




Fig. 2: The IR spectrum of Amberlite XAD-4 and AXAD4-8HQ resin

### 3.2.2. TGA characterization

The TGA experiments were conducted for plain AXAD-4 and AXAD-4-8HQ resin at a heating rate of  $10\text{ }^{\circ}\text{C}/\text{min}$  from ambient temperature to  $900\text{ }^{\circ}\text{C}$  in flow of  $\text{N}_2$ . The TGA curves for the bare AXAD-4 and AXAD-4-8HQ resin are represented in (Fig. 3). The thermogram of plain AXAD-4 polymer, exhibited clear mass degradation over

the temperature range 320 - 895 °C (100 %). On the other hand, the TGA of chelating resin; AXAD-4-8HQ, displayed two step weight losses up to 645 °C. The resin has lost about 12 % of its original weight at 220-330 °C as a result of displacement of 8-HQ moieties out of the polymer. The weight loss after 330 °C (88 %) could be associated to the dissociation of polymeric matrix (Pacurariu et al., 2013; Gladis & Rao, 2002).




Fig. 1: TGA Thermogram of AXAD-4 and AXAD-4-8HQ resin.

### 3.2.3. XPS characterization

The chemical bonding of 8HQ moiety onto the AXAD4 surface has been ascertained using X-ray photoelectron spectroscopic (XPS) technique. XPS analysis is reliable approach to confirm the successfulness of modification of AXAD-4 with 8-HQ. The survey spectra of AXAD-4 and AXAD4-8HQ resin is shown in (Fig .4). It was clear from (Fig .4) that the XPS spectrum of AXAD4-8HQ showed peaks for N1s (two components peaks of pyridinic N at 398.08 eV and 400.08 eV corresponds to (N=N), which arose from the present of 8-HQ ligands and its linkage on the AXAD-4

surface. The clear existence of N (from the 8-HQ) from the spectrum strongly indicates that the 8-HQ molecule is covalently bonded to the AXAD-4 surface (Kosa et al., 2012).




Fig. 2: XPS spectra of a) AXAD-4 and b) AXAD4-8HQ resin

### 3.3. Chelator sorption capacity

The sorption capacity of a resin is a key factor to estimate the required mass of sorbent resin to achieve quantitative extraction/ preconcentration of the elements from a given sample matrix. The calculated sorption capacity (SC) values in mmol/g unit for Co, Ni and Cu were shown in 3 replicates at pH 6 and compared with sorption capacity for unmodified AXAD-4 under the same condition as seen in (Fig. 5). It is clear from ( Fig. 5), the sorption capacity for AXAD4-8HQ resin was improved by more than (95.90% for Co), (87.13% for Ni) and (99.28% for Cu) in comparison with the unmodified AXAD-4 for the investigated ions (Vassileva & Furuta, 2003).




Fig. 5: Sorption capacity for XAD-4 and AXAD4-8HQ resin.

The comparison of sorption capacity values of the XAD4-8HQ chelating resin with other amberlite resins functionalised with 8-HQ chelating agent (**Table1**) revealed that the XAD4-8HQ chelator exhibits higher sorption values (at least twice) for the investigated metal ions. This finding could be ascribed for the high surface area of XAD-4 and the efficiency of the chemical functionalisation used in this work.

Table 1: comparison of sorption capacity of the synthesised chelator with other 8-HQ-amberlite resins for Co, Ni, Cu metal ions.

Adsorbent	Metal ions (mM/g)			Refs.
	Co	Ni	Cu	
Amberlite XAD-7	-	0.011	0.018	Lee et al. (1988)
Amberlite XAD-2000*	0.115	0.132	0.148	Duran et al. (2007)
Amberlite XAD-2010*	0.161	0.187	0.136	Gundogdu et al. (2007)
Amberlite IR-120*	-	-	0.038	Sadia et al. (2016)
Amberlite XAD-4	0.366	0.265	0.328	Current work

\* the unit was converted from (mg/g) to (mM/g) by division on atomic weight for metal.

### 3.4. The effect of solution pH

The pH of solution plays a significant role in SPE studies because most metal chelating ligands are conjugate bases of weak acids with a very strong tendency for (H) ions. The removal percentage of the studied metals plotted versus pH as presented in (Fig. 6). The maximum sorption for Co and Ni were 96.42% and 97.06 % at pH 8 meanwhile Cu ion reached its optimal removal percentage ( 85.76 %) at pH 6. The effect of pH on the sorption of metal ions by immobilized 8-HQ chelator may be influenced by the behavior the chelating agent in the acidic media and basic media. i.e., at low pH values, the nitrogen of heterocyclic ring of 8-HQ is protonated whilst the phenolic OH group dissociates in the alkaline environment. Accordingly, the ligand tends to chelate with the metal ions under slightly alkaline conditions because the chance for the formation of more stable complexes is better. Hence, pH 8 is an adequate for the extraction of Co, Ni by this chelator, meanwhile pH 6 is optimal to form stable complex with Cu. These pH values were chosen as optimal in the further experiments (Islam et al., 2010).




Fig. 6: Effect of pH on the removal of Co, Ni and Cu from Amberlite XAD-4-8HQ resin.

### 3.5. The effect of contact time

The effect of contact time is a significant parameter for the quantitative retention of analytes by SPE chelator. The removed percentage of the investigated metal ions as a function of time is shown in (Fig. 7). The data represented in (Fig. 7) illustrate that the chelating resin uptake 50% of Co and Cu after 10 minutes, however only 27% of Ni is removed during this time. However, an equilibration time of 60 minutes was effective for the resin to absorb about 85% of Cu and Co, and almost 80 % of Ni ( Xie et al., 2008).




Fig. 7: Effect of contact time on the removal of Co, Ni and Cu from Amberlite XAD-4-8HQ resin

### 3.6. Stability and reusability of chelator

Stability and reusability of SPE materials are viable characteristics to gauge the sustainability and economic efficiency of sorbents. In this article, the chelator stability

was evaluated using our previous methods (AlSuhaimi, 2019; AlSuhaimi et.al, 2019). Briefly, the chelator was treated with acidic and alkaline solutions of different concentrations and its sorption capacity determined for the tested metal ions. The results have shown that the chelator can withstand for concentration of nitric acid up to 3 M  $\text{HNO}_3$  without exhibiting any significant diminution in the value of sorption capacity (i.e., the maximum reduction is below 2.7%). However, the treatment of chelating resin with more concatenated acid ( $\geq 4$  M  $\text{HNO}_3$ ), results in a reduction in sorption by about 8% of the original value. Also, a reddish coloration was observed in solution, which could be ascribed to the detachment of the chelating moieties along with the linkage molecules from the XAD beads. Similarly, the material was soaked in alkaline solution pH12 (the pH value adjusted using ammonium solution) and its sorption capacity was tested. Yet, no significant change in sorption capacity being observed. The reusability of the chelating resin has been evaluated by determining its sorption capacity for the investigated metal ions after 50 loading and elution cycles. It was found that there is no substantial change in sorption capacity and hence, it can be reused several times and it is appropriate for dynamic SPE processing. Furthermore, the chelating resin show no significant variation in sorption capacity upon storage in the desiccator for more than 8 months in the laboratory.

### **3.7. Method Application: The Analysis of Groundwater Real Samples**

The SPE method using the prepared metal chelator has been used for the preparation of groundwater samples prior to the analysis of the selected elements with ICP-MS. The groundwater samples were collected from 5 narrow mouth well of depth ranged from 130 to 170 m within Swary valley (upper catchment AlWadi AlMubarak), AlMadina Almonawarah province. The samples (1 L) were acidified, filtered in field and transported to laboratory in iceboxes (see map in Fig. 8).




Fig. 8: Sampling sites from Swary Valey, AlMadinah AlMunawarah.

Prior to the ICP-MS analysis 25 ml of groundwater samples were prepared using SPE protocol described in section 2.8. The concentration of the analyzed metals; Co, Ni and Cu, in real samples, along with the recovery for the spiked samples are presented in (**Table 2**). The recoveries as estimated from the addition of concentrations of spikes to water samples were in the range (96.4%-99.8%, 97.8%-99.6% and 94.4%-115.4%) for Co, Ni and Cu respectively. Thus, the proposed method has proved to be an efficient sample treatment procedure during the simultaneous analysis of trace metals in groundwater real samples.

Table 2: Trace metals contents of real water samples with the proposed method  
(mean conc.  $\pm$ RSD (ng ml<sup>-1</sup>))

Sample	Metals	Added (ng/ml)	Found +RSD (ng/ml)	Recovery (%)
1	Co	0	1.21 $\pm$ 0.48	96.4%
		5	6.03 $\pm$ 1.66	
	Ni	0	0.97 $\pm$ 1.60	97.82%
		5	5.86 $\pm$ 1.20	
	Cu	0	2.04 $\pm$ 0.83	105.41%
		5	7.31 $\pm$ 1.31	
2	Co	0	1.24 $\pm$ 1.37	96.62%
		5	6.07 $\pm$ 1.29	
	Ni	0	1.12 $\pm$ 0.98	97.81%
		5	6.01 $\pm$ 1.76	
	Cu	0	1.97 $\pm$ 0.56	103.05%
		5	7.12 $\pm$ 1.97	
3	Co	0	1.15 $\pm$ 0.9/	98.81%
		5	6.09 $\pm$ 1.28	
	Ni	0	0.95 $\pm$ 1.16	99.20%
		5	5.91 $\pm$ 1.86	
	Cu	0	2.27 $\pm$ 0.88	97.81%
		5	7.16 $\pm$ 1.08	
4	Co	0	1.17 $\pm$ 0.94	98.04%
		5	6.07 $\pm$ 1.18	
	Ni	0	1.03 $\pm$ 1.65	99.61%
		5	6.01 $\pm$ 1.10	
	Cu	0	2.15 $\pm$ 0.47	94.41%
		5	6.87 $\pm$ 1.167	
5	Co	0	1.32 $\pm$ 0.83	99.81%
		5	6.31 $\pm$ 1.83	
	Ni	0	1.04 $\pm$ 1.92	99.61%
		5	6.02 $\pm$ 0.18	
	Cu	0	2.19 $\pm$ 1.50	115.40%
		5	7.96 $\pm$ 1.38	

Sample volume 25 ml, eluent 1.5 M HNO<sub>3</sub>

#### **4. Conclusion**

The developed chemical modification reported in this article enabled the synthesis of AXAD-4-8HQ metal chelator by aryl radical addition of aniline to the XAD-4 surface followed by diazotization step to couple 8-HQ moieties. ATR-IR, TGA and XPS analysis confirmed the success of resin synthesis. The most important parameters influencing SPE process e.g., the effect of pH and contact time of metals with sorbent have been investigated. It was found that resin could extract about 96.42 and 97.06 % of Co for Ni at pH 8, and 85.76 % for Cu at pH 6. Contact time experiments showed that the equilibration time of 60 min was found to be effective for maximum sorption of Co, Ni and Cu. The chelator exhibited relatively higher sorption capacity in comparison with 8-HQ immobilized onto other amberlite substrates using classical nitration/diazotization chemical modifications. Noticeably, although the 60 minutes equilibration time seems to be relatively long, the resin works well as SPE material in dynamic mode using the standard SPE manifold in the examined concentration range. This also has been established by the application of the new metal chelator as an efficient SPE material for sample preparation of trace metals from groundwater real samples of high to moderate salinity.

#### **Acknowledgments**

The authors are grateful for King Abdul-Aziz City for Science & Technology (KACST) for financial support (grant No: 1-17-01-006-0003).

## References

- Abiman, P., Wildgoose, G. G., & Compton, R. G. (2008). A mechanistic investigation into the covalent chemical derivatisation of graphite and glassy carbon surfaces using aryldiazonium salts, *J. Phys.Org. Chem.*, 21, 433–439.
- Ahmad, A., Siddique, J. A., Laskar, M. A., Kumar, R., Mohd-Setapar, S. H., Khatoon, A., & Shiekh, R. A. (2015). New generation Amberlite XAD resin for the removal of metal ions, *J. Envir.Sci.*, 31, 104–123.
- Alqadhi, N. F., & Alsuhaimi, A. O. (2020). Chemically functionalized activated carbon with 8-hydroxyquinoline using aryldiazonium salts / diazotization route : Green chemistry synthesis for oxins-carbon chelators, *Arab.J.Chem.*, 13(1), 1386-1396.
- AlSuhaimi, A. O., (2019). Preparation of Silica-4-(2-pyridylazo) Resorcinol Chelator for Solid Phase Extraction of Transition Metals from Groundwater, *Chem. Soc., Pak.* 41(1),151-160
- AlSuhaimi, A. O., AlRadaddi, S. M., Al-Sheikh Ali, A. K., Shraim, A. M., & AlRadaddi, T. S. (2019). Silica-based chelating resin bearing dual 8-hydroxyquinoline moieties and its applications for solid phase extraction of trace metal from seawater prior to thier analysis by ICP-MS, , *Arab. J. Chem.*12(3), 360-369.
- Armstrong, R. D., Todd, M., Atkinson, J. W., & Scott, K. (1996). Selective electrodeposition of metals from simulated waste solutions, *J. Appl. Electrochem.*, 26, 379–384.
- Bazrafshan, E., Mohammadi, L., Ansari-Moghaddam, A., & Mahvi, A. H. (2015). Heavy metals removal from aqueous environments by electrocoagulation process, *J Environ Health Sci Eng.*, Oct.,13, 74.
- Brown, R. J. C., & Milton, M. J. T. (2005). Analytical techniques for trace element analysis, *Trend Anal.Chem.*, 24, 266–274.
- Cheira, M. F. (2015). Synthesis of pyridylazo resorcinol – functionalized Amberlite XAD-16 and its characteristics for uranium recovery. *J. Environ. Chem. Eng.*, 3, 642–652.
- Dabrowski, A. (1998). Adsorption and its Applications in Industry and Environmental Protection (Vol. 120),Elsevier Science, Amesterdam, Netherlands, pp. 75-275.
- Dabrowski, A., Hubicki, Z., Podkoscielny, P., & Robens, E. (2004). Selective removal of the heavy metal ions from waters and industrial wastewaters by ion-exchange method. *Chemosphere*, 56, 91–106.
- Duran, C., Senturk, H. B., Gundogdu, A., Eici, L., Soylak, M., Tufekci, M. & Uycur, Y.(2007). Determination of Some Trace Metals in Environmental Samples

- by Flame AAS Following Solid Phase Extraction with Amberlite XAD-2000 Resin after Complexing with 8-Hydroxyquinoline, *Chin. J. Chem.*, 25, 196–202
- Fan, J., Wu, C., Wei, Y., Peng, C., & Peng, P. (2007). Preparation of xylenol orange functionalized silica gel as a selective solid phase extractor and its application for preconcentration - separation of mercury from waters, *J. Hazard. Mater.*, 145, 323–330.
- Gao, B., Zhang, J., & Guo, J. (2010). Synthesis of salicylic acid-polystyrene type chelate resin with a new route, *J. Polym. Res.*, 17, 301–308.
- Gladis, J. M., & Rao, T. P. (2002). Quinoline-8-ol-immobilized Amberlite XAD-4: Synthesis, characterization, and uranyl ion uptake properties suitable for analytical applications, *Anal. Bioanal. Chem.*, 373, 867–872.
- Golshaei, R., Shemirani, F., & Davudabadi Farahani, M. (2015). Combination of solid phase extraction based on nano alumina and liquid-liquid extraction for selective determination of palladium in food samples. *J. Anal. Chem.*, 70, 310–315.
- Gundogdu, A., Duran, C., elal, H., Senturk, B., Elci, L. & Soylak, M., (2007). Simultaneous Preconcentration of Trace Metals in Environmental Samples Using Amberlite XAD-2010/8-Hydroxyquinoline System, *Acta Chim. Slov.*, 54, 308–316
- Hu, B., & He, M. (2012). Pre-concentration and Sample Treatment Techniques for Trace Element Analysis; in *Comprehensive Sampling and Sample Preparation* Pawliszyn, J. (Edit) . Elsevier Inc, Amsterdam, Netherlands, pp367-390.
- Huck, C. W., & Bonn, G. K. (2000). Recent developments in polymer-based sorbents for solid-phase extraction. *J. Chromatogr. A*, 885, 51–72.
- Islam, A., Laskar, M. A., & Ahmad, A. (2010). Characterization and Application of 1-(2-Pyridylazo) -2-naphthol Functionalized Amberlite XAD-4 for Preconcentration of Trace Metal Ions in Real Matrices, *J. Chem. Eng. Data*, 5553–5561.
- Jung, K. H., Byun, J. H., Lee, Y. S., & Park, S. J. (2010). Synthesis and characterization of chemically modified polystyrene as processable carbon fiber precursors, *Res. Chem. In*, 36, 621–627.
- Kempegowda, R. G., & Malingappa, P. (2013). Diazonium functionalized exfoliated graphitic carbon as a binderless and covalently modified electrochemical interface for mercury sensing. *Sens. Actuator B.-Chem*, 186, 478–485.
- Khan, M. S., Zaidi, A., Goel, R., & Musarrat, J. (2011). *Bio-management of Metal-Contaminated Soils*. Springer Science, Heidelberg, Germany, pp.183-323.
- Korn, M. D. G. A., De Andrade, J. B., De Jesus, D. S., Lemos, V. A., Bandeira, M. L. S. F., Dos Santos, W. N. L., Ferreira, S. L. C. (2006). Separation and preconcentration procedures for the determination of lead using spectrometric techniques, *Talanta*, 69, 16–24.
- Kosa, S. A., Al-Zhrani, G., & Abdel Salam, M. (2012). Removal of heavy metals from aqueous solutions by multi-walled carbon nanotubes modified with 8-hydroxyquinoline, *Chem. Eng.*, 181–182, 159–168.
- Lee, M. D. W., Eum, C. H., Lee, I. H. & Jeon S. J. (1988). Adsorption Behavior of 8-

Hydroxyquinoline and Its on Amberlite XAD Resins, and Adsorption of Metal Using Chelating Agent-Impregnated Resins, *Anal. Sci.*, 4, 505-510.

- Lichtfouse, E., Schwarzbauer, J., & Robert, D. (2013). *Green Materials for Energy, Products and Depollution*. Springer Science, Dordrecht, Germany, pp.151-228.
- Liu, R., Ruan, T., Wang, T., Song, S., Guo, F., & Jiang, G. (2014). Determination of nine benzotriazole UV stabilizers in environmental water samples by automated on-line solid phase extraction coupled with high-performance liquid chromatography–tandem mass spectrometry, *Talanta*, 120, 158–166.
- Liu, Y., Guo, Y., Chang, X., Meng, S., Yang, D., & Din, B. (2004). Column Solid-Phase Extraction with 2-Acetylmercaptophenyldiazoaminoazobenzene (AMPDAA) Impregnated Amberlite XAD-4 and Determination of Trace Heavy Metals in Natural Waters by Flame Atomic Absorption Spectrometry, *Microchim. Acta*, 149, 95–101.
- Liu, Y., Guo, Y., Meng, S., & Chang, X. (2007). Online separation and preconcentration of trace heavy metals with 2,6-dihydroxyphenyldiazoaminoazobenzene impregnated amberlite XAD-4. *Microchim. Acta*, 158, 239–245.
- Mendil, D., Karatas, M., & Tuzen, M. (2015). Separation and preconcentration of Cu(II), Pb(II), Zn(II), Fe(III) and Cr(III) ions with coprecipitation method without carrier element and their determination in food and water samples, *Food Chem.*, 177, 320–324.
- Nezhati, M. N., Panahi, H. A., Moniri, E., Kelahrodi, S. R., Assadian, F., & Karimi, M. (2010). Synthesis, characterization and application of allyl phenol modified amberlite XAD-4 resin for preconcentration and determination of copper in water samples, *Korean J. Chem. Eng.*, 27, 1269–1274.
- Nickerson, B. (2011). *Sample Preparation of Pharmaceutical Dosage Forms: Challenges and Strategies for Sample Preparation and Extraction*. Springer Science, Heidelberg, Germany pp.43-345.
- Pacurariu, C., Mihoc, G., Popa, A., Muntean, S. G., & Ianos, R. (2013). Adsorption of phenol and p-chlorophenol from aqueous solutions on poly (styrene-co-divinylbenzene) functionalized materials, *Chem. Eng*, 222, 218–227.
- Pandurangappa, M., & Raghu, G. K. (2011). *Chemically Modified Carbon Nanotubes : Derivatization and their Applications*, Intech Open Access publisher, pp.500-522.
- Sadia, M., Jan, M. R., Shah, J. & Haq, A., (2016). Comparison of simple and chelated amberlite IR-120 for preconcentration and Determination of Cu(II) from aqueous samples, *Bull. Chem. Soc. Ethiop.*, 30(1),39-54.
- Saxena, R., & Meena, P. L. (2014). Flow injection online solid phase extraction system using Amberlite XAD-16 functionalized with 8-hydroxyquinoline for copper and zinc determination by flame atomic absorption spectrometry. *RSC Adv.*, 4, 20216–20225.
- Saylam, A., Seferoğlu, Z., & Ertan, N. (2014). Azo-8-hydroxyquinoline dyes: The synthesis, characterizations and determination of tautomeric properties of some new phenyl- and heteroarylazo-8-hydroxyquinolines, *J. Mol. Liq.*, 195, 267–276.

- Scheuerman, R. A., & Tumelty, D. (2000). The reduction of aromatic nitro groups on solid supports using sodium hydrosulfite ( $\text{Na}_2\text{S}_2\text{O}_4$ ), *Tetrahedron Lett.*, 41, 6531–6535.
- Shemirani, F., & Yousefi, S. R. (2007). Selective extraction and preconcentration of cerium(IV) in water samples by cloud point extraction and determination by inductively coupled plasma optical emission spectrometry, *Microchim. Acta*, 157, 223–227.
- Soylak, M., Divrikli, U., Saracoglu, S., & Elci, L. (2007). Membrane filtration - Atomic absorption spectrometry combination for copper, cobalt, cadmium, lead and chromium in environmental samples, *Environ. Monit. Assess.*, 127, 169–176.
- Srivastava, S., & Goyal, P. (2010). *Novel Biomaterials Decontamination of Toxic Metals from Wastewater*, Springer-Verlag, Berlin, Germany, pp.111-122.
- Uzun, A., Soy lak, M., & Elci, L. (2001). Preconcentration and separation with Amberlite XAD-4 resin ; determination of Cu , Fe , Pb , Ni , Cd and Bi at trace levels in waste water samples by flame atomic absorption spectrometry, *Talanta*, 54, 197–202.
- Vassileva, E., & Furuta, N. (2003). Application of iminodiacetate chelating resin muromac A-1 in on-line preconcentration and inductively coupled plasma optical emission spectroscopy determination of trace elements in natural waters. *Spectrochim. Acta B*, 58, 1541–1552.
- Wang, J., Hansen, E. H., & Miró, M. (2003). Sequential injection-bead injection-lab-on-valve schemes for on-line solid phase extraction and preconcentration of ultra-trace levels of heavy metals with determination by electrothermal atomic absorption spectrometry and inductively coupled plasma mass, *Anal. Chim. Acta*, 499, 139–147.
- Wegscheider, W., & Knapp, G. (1981). Preparation of Chemically Modified Cellulose Exchangers and their use for the Preconcentration of Trace Elements, *Crit Rev. Anal Chem* 11, 79–102.
- Wildgoose, G. G., Leventis, H. C., Davies, I. J., Crossley, A., Lawrence, N. S., Jiang, L., Compton, R. G. (2005). Graphite powder derivatised with poly- L -cysteine using “ building-block ” chemistry - a novel material for the extraction of heavy metal ions, *J. Mater. Chem.*, 15, 2375–2382.
- Xie, F., Lin, X., Wu, X., & Xie, Z. (2008). Solid phase extraction of lead ( II ), copper ( II ), cadmium ( II ) and nickel ( II ) using gallic acid-modified silica gel prior to determination by flame atomic absorption spectrometry. *Talanta*, 74, 836–843.
- Zhai, Y., Duan, S., He, Q., Yang, X., & Han, Q. (2010). Solid phase extraction and preconcentration of trace mercury(II) from aqueous solution using magnetic nanoparticles doped with 1,5-diphenylcarbazine, *Microch. Acta*, 169, 353–360.
- Zhao, R.-S., Hu, C., Zhou, J.-B., Yuan, J.-P., Wang, S.-S., & Wang, X. (2011). Preconcentration and sensitive determination of hexabromocyclododecane diastereomers in environmental water samples using solid phase extraction with bamboo charcoal cartridge prior to rapid resolution liquid chromatography – electrospray tandem mass spec. *Anal. Bioanal Chem*, 400, 1189–1195.