

Synthesis, Characterization of Ag/TiO₂ Nanocomposite: Its Anticancer and Anti-Bacterial Activities

S. Jafar Ali Ibrahim¹, S. Rajasekar² N. S. Kalyan Chakravarthy³ Varsha⁴


Maninder Pal Singh⁵, Vaneet Kumar⁴ and Saruchi⁵

^{1,3}QIS College of Engineering and Technology, Ongole, AP, India - 523 272

²QIS Degree and PG College, Ongole, AP, India - 523 272

⁴Department of Applied Sciences, CT Institute of Engineering, Management and Technology, Shahpur Campus Jalandhar, Punjab, India, ⁵Department of Biotechnology, CT Institute of Pharmaceutical Sciences, Shahpur Campus, Jalandhar, Punjab

GRAPHICAL ABSTRACT



Abstract

TiO₂ nanomaterials have gained much interest due to their importance of wide area application. In this study, TiO₂ nanocomposites were modified with Ag NPs by the stober method. The synthesized nanocomposites were characterized by XRD, FTIR, scanning electron microscope (SEM) and energy dispersive X-ray spectroscopy (EDAX), UV-DRS. Antibacterial activities were determined against the bacterial pathogens as well as *in vitro* cancer cell lines and significant of nanocomposite's anticancer activity were analyzed. Ag/TiO₂ nanocomposite possesses efficient cytotoxic activity towards the A549 cell lines and can be used further for *in vivo* trials. Ag/TiO₂ nanocomposites showed good antibacterial activity against different strains of bacteria *Staphylococcus aureus*, *Shigella flexneri* and *Bacillus sp.* The zone of inhibition was found to be higher in synthesized Ag/TiO₂ nanocomposites as compared to standard antibiotic streptomycin.

Keywords: Nanomaterials, TiO₂, Bacteria, Strains, Antibacterial

1 Introduction

In recent times, industrial wastewater treatment has become a critical issue due to its damaging and overwhelming effects on our environment and the environment.

For the past few decades, much research has been conducted to explore the nanomaterial which focuses on synthesis methods, characterization, components, and applications in various interdisciplinary fields. Nowadays, nanomaterials are widely used in medical fields such as drug delivery, implants, coating, antibacterial activity etc. Silver-based nanomaterials are attractive to the researchers due to their antibacterial activity, as they generally possess excellent mechanical properties and can release heavy metal ions to cause damage to bacterial DNA [1-4]. Silver and titanium dioxide nanomaterials have been explored by many researchers as they can

be synthesized through various methods such as Sol-Gel, Micelle, and Inverse Micelle, Hydrothermal, Solvothermal, Electrode position, Chemical Vapor Deposition, Physical Vapor Deposition, HVPG, and Sonochemical [5 -8].

Titanium dioxide containing silver synthesized by different methods with excellent photo catalytic activities can efficiently be used to degrade R6G dyed, water purification, medical applications virus inactivation, self-cleaning and food safety/sensing [9-15]. The studies reported that silver-titanium dioxide nanocomposites materials are widely known for their anti-pathogenic ability. As an antibacterial agent with efficacy against various strains of Gram-positive bacteria (*B. subtilis*, *S. aureus*, MRSA), Gram Negative bacteria (*E. coli*, *K. pneumoniae*, *P. aeruginosa*), and fungi (*C. albicans*) [16].

Nanomaterials containing Ag are well-known as an effective antibacterial activity. The extract of Ag ion is the most biologically efficient viral study of bacterial, and fungi. Metallic Ag nanoparticles catch the attention of great interest in recent years on clarification of their omission of antimicrobial competence.

Some studies also indicate that antibacterial activity increased with increase concentration of TiO₂-SiO₂-Ag nanocomposites and the elevated concentrations were able to bring about complete inhibition of bacterial cells.

This study aims to explore and reveal the mechanical properties of silver and titanium dioxide nanocomposites materials with anti-bacterial capabilities. In this current study, we used the stober method to synthesize Ag/TiO₂ nanocomposites.

2 Materials and methods

2.1 Synthesis of Ag/TiO₂ Nano composite




Figure 1 Synthesis of Ag/TiO₂ nanocomposite

The silver colloids were synthesized by chemical reduction method in alkaline environment using L-Ascorbic Acid as reducing agent, N, N, N, N- Cetyl Trimethyl Ammonium Bromide (CTAB) as capping agent and Silver Nitrate solution as precursor. The CTAB is added to silver nitrate solution and stirred for half an hour and L-ascorbic acid solution is added to reduce the silver nitrate solution to silver nanoparticles. The pH of the prepared silver colloid is adjusted to 6.6-7.0 by adding ammonium hydroxide solution. Titania was grown onto the surface of silver nanoparticles to form Ag/TiO₂ nanocomposite by means of the Stober method. The silver colloid is mixed with 200ml of anhydrous ethanol and allowed to stir for an hour. After stirring for an hour, 5ml of titanium iso prop oxide was added. The

solution containing silver colloid, ethanol and titanium iso prop oxide is continuously stirred for 24h. The solution after 24h of continuous stirring is dried in the oven at 60°C to obtain the Ag/TiO₂ nanocomposite. If required the obtained nano powder can be sintered at 400°C for 4h to make it further dry and to remove moisture content. The typical conditions used in this work are: [AgNO₃] = 0.1M, [C₆H₈O₆] = 0.1M, [C₁₉H₄₂BrN] = 0.1g, [NH₄ (OH)₂] = 0.5M. The growth condition used here is: [C₂H₅OH] = 200ml and [titanium isopropoxide] = 5ml. Figure 1 shows the schematic of the synthesis of Ag/TiO₂ nanocomposite [17 - 21].

3 Results and Discussion

3.1 X-Ray diffraction studies

The X-ray diffraction measurements were carried out to study the crystalline quality and crystallographic orientation of the Ag/TiO₂ nanocomposites. Figure 2 shows the XRD pattern of Ag/TiO₂ and exhibits characteristic peaks at $2\theta=25.37^\circ$, 48.12° , 53.97° and 55.10° , corresponding to (101), (200), and (105) planes, respectively, which belong to typical anatase-TiO₂ materials (JCPDS no.89–4203). The sharp and narrow diffraction of the peaks demonstrated that all Ag/TiO₂ was of good crystalline in quality. This X-ray diffraction data is used to determine dimensions of unit cell, crystal structure, texture coefficient, standard deviation, crystalline and the calculated crystalline parameters are listed in Table 1. The grain size of the crystallite is calculated using Scherrer's formula and the average crystallite size is calculated from the broadening of the corresponding sharp peaks in Ag/TiO₂ and found to be 37.66 nm [22],




Figure 2 X-Ray Diffraction patterns of Ag/TiO₂ Nanocomposites

Table1 Structural Properties of Ag/TiO₂ Nanocomposites

Ag/ TiO ₂	2 θ		d		Crystal Size (nm)	Lattice constant A°	
	(Std)	(Obs)	(Std)	(Obs)		JCPDS 89-4203	(Obs)
101	25.304	25.475	3.517	3.497	34.74	a=3.785	a = 3.810
200	48.037	48.256	1.892	1.886	40.61	c= 9.514	c= 9.112

3.2 FTIR Analysis

Figure 3 shows the FT-IR spectrum of the synthesized samples. The peak 2933 cm⁻¹ shows the CH₂ bending vibration. Wave number 1633 cm⁻¹ indicates the presence of C=C stretching vibrations. The peak value 552 cm⁻¹ in the Ag/TiO₂ sample indicates the Ti-O stretching vibrations [23].




Figure 3 FTIR spectrum of Ag/TiO₂

3. 3 SEM and EDX Analysis

The morphological purpose of Ag/TiO₂, SEM analysis was made and it recognized that the samples are spherical in nature. Figure 4 showed that Ag/TiO₂ nanoparticles were with a number of aggregates respectively and it revealed that the nanoparticles are spherical in nature. The elemental dispersive analysis (EDX) completes the chemical profile of the Ag/TiO₂, the chemical profile was noted as 60.58 % of titanium and 10.58% of Ag.




Figure 3a SEM and EDAX analysis of Ag/TiO₂

3.4 Analysis of Particle Size by Particle Size Analyzer: PSA

Figure 4 shows the particle size distribution of Ag/TiO₂. The dispersive medium for the sample is prepared by tri ethanolamine and deionized water in the ratio 1:3. 3g of prepared samples were dispersed in the dispersive medium by **sonication of the** mixture for duration of 10 min. The particle size measurement increases with increasing time period and temperature conditions. From the figure 3.5, it is found that the particle size distribution of Ag/TiO₂ 75.94 nm.




Figure 4 Particle size distribution of Ag/TiO₂

3.5 Absorption Spectrophotometer (UV-DRS)

Figure 5 and show the UV-DRS analysis of Ag/TiO₂. UV-DRS reflectance mode measurement is one of the powerful techniques in determining the optical properties of powder form of samples. It measures the wavelength of light when it reflects the UV light rays. The reflection band of Ag/TiO₂ is obtained as 330 nm from figure 3.6 and the band gap energy was calculated to be 3.75 eV and also confirmed that the synthesized nanocomposites are wide band gap semiconducting materials




Figure 5 UV-DRS analysis of Ag/TiO₂

3.6 Antibacterial activity of Ag/TiO nanoparticles

The antibacterial activity of Ag/TiO nanoparticles was analyzed in vitro using a well diffusion method. The bactericidal effect was confirmed in contradiction of gram negative bacteria *S. flexneri* and gram positive pathogens like *S. aureus* and *Bacillus sp.* The antibacterial activity of Ag/TiO₂ nanocomposites was given in Table 2. Previous studies reported that TiO₂ nanotubes own antimicrobial accomplishment, and the device involves a prompt and reversible substantial first phase, and a cellular second phase [24-29]. Another study compared the antibacterial activity of Ti substrate with Ti coated with EG, PEG 400, PEG 600 and PEG 1000 against *E. coli*. Among these, Ti substrate showed little activity [30]. This reveals that Ti substrate has not much antibacterial activity. Studies about the bactericidal activity of ZrO₂ nanoparticles disclosed that they exhibit greater activity against *S. aureus* and *B. subtilis* [31]. These studies reveal that the Ag/TiO₂ nanocomposites activity towards bacteria leads to an inhibition zone even greater than standard antibiotics [33-35].

Table 2 Antimicrobial activity of Ag/TiO₂ treated against bacterial pathogens

Test organisms	Zone of inhibition in millimeter (in diameter)	
	Ag/TiO ₂	Standard Streptomycin 30μg
<i>Staphylococcus aureus</i>	24	34
<i>Shigella flexneri</i>	32	29
<i>Bacillus sp</i>	38	32

Solvent used : DMSO (Dimethyl Sulphoxide) **Standard used :** Streptomycin 30 µg.

3.7 Cytotoxicity Behavior

The significant candidate of anticancer drugs is the ability to induce tumor cell apoptosis. The basic cytotoxic assay to assess anticancer activity is the MTT assay. In the present study, various Ag/TiO₂ nanocomposites were treated against A549 cell lines. The percentage of cell viability was gradually decreased against increasing concentration of nanoparticles Table 3 Ag/TiO₂ nanoparticles showed obvious results against A549 cell lines. The nanoparticles showed good activity against A549 cells even at lower concentration like 7.8 µg/ml. The IC₅₀ value of Ag/TiO₂ nanoparticles is 49.79. This indicated that nanoparticles showed intense activity against the A549 cell line. A recent study [33] showed the anticancer activity of TiO₂ nanoparticles against A549 cells, which confirmed that cell viability decreased only after 72 hrs of treatment. But in the present study, the results illustrated that Ag/TiO₂ nanoparticles impart cytotoxic effects towards the A549 cell line with 24 hrs treatment. It is evident that the Ag/TiO₂ nanocomposite possesses efficient cytotoxic activity towards the A549 cell lines. This indicated that Ag/TiO₂ nanocomposite can be further tested for *in vivo* trials.

Table 3 Anticancer effect Ag/Ti O₂ on A549 cell line

S.No.	Concentration (µg/ml)	Dilutions	Absorbance (O.D)	Cell Viability (%)
1	1000	Neat	0.062	12.50
2	500	1:1	0.107	21.57
3	250	1:2	0.165	33.26
4	125	1:4	0.204	41.12
5	62.5	1:8	0.247	49.79
6	31.2	1:16	0.316	63.70
7	15.6	1:32	0.375	75.60
8	7.8	1:64	0.413	83.26
9	Cell control	-	0.496	100

4 Conclusions

Ag/TiO₂ nanocomposites have been successfully synthesized by the Stober method. The XRD analysis confirmed that synthesized nanocomposites are crystalline in nature and the average calculated crystallite size was found to be 37.66 nm. UV-DRS characterization of the prepared nanocomposites shows that the band gap energy of Ag/TiO₂ is 3.75 eV and confirms that the prepared nanocomposites is a wide band gap semiconducting material. The synthesized NPs showed great activity against the bacterial pathogens as well as *In Vitro*

cancer cell lines. An Ag/TiO₂ nanocomposite possesses efficient cytotoxic activity towards the A549 cell line and can be used further for *in vivo* trials. Ag/TiO₂ nanocomposite showed good antibacterial activity against different strains of bacteria *Staphylococcus aureus*, *Shigella flexneri* and *Bacillus sp.* The zone of inhibition was found to be higher in synthesized Ag/TiO₂ nanocomposite as compared to standard antibiotic streptomycin. Foregone discussion showed that these NPs can be considered further for *in vivo* studies

References

- [1] M. Goudarzi, N. Mir, M. Mousavi-Kamazani, S. Bagheri, M. Salavati-Niasari, Biosynthesis and characterization of silver nanoparticles prepared from two novel natural precursors by facile thermal decomposition methods, *Sci. Rep.* 6 (2016) 1-13.
- [2] M.A. Muflikhun, G.B. Castillon, G.N.C. Santos, A.Y. Chua, Micro and nano silver-graphene composite manufacturing via horizontal vapor phase growth (HVPG) technique, *Mater. Sci. Forum* 901 (2017) 3-7. Trans Tech Publications.
- [3] O. Amiri, S. Bagheri, M. Mazaheri, M. Salavati-Niasari, M. Farangi, Stable plasmonic-improved dye sensitized solar cells by silver nanoparticles between titanium dioxide layers, *Electrochim. Acta* 152 (2014) 101-107.
- [4] M.J. Hajipour, K.M. Fromm, A. Akbar Ashkarran, D. Jimenez de Aberasturi, I.R. de Larramendi, T. Rojo, et al., Antibacterial properties of nanoparticles, *Trends Biotechnol.* 30 (2012) 499-511.
- [5] P. Zhang, I. Wyman, J. Hu, S. Lin, Z. Zhong, Y. Tu, et al., Silver nanowires: synthesis technologies, growth mechanism and multifunctional applications, *Mater. Sci. Eng. B Solid State Mater. Adv. Technol.* 223 (2017) 1-23.
- [6] K. Zheng, M.I. Setyawati, D.T. Leong, J. Xie, Antimicrobial silver nanomaterials, *Coord. Chem. Rev.* 357 (2018) 1-17.
- [7] A. Besinis, T. De Peralta, R.D. Handy, The antibacterial effects of silver, titanium dioxide and silica dioxide nanoparticles compared to the dental disinfectant chlorhexidine on *Streptococcus mutans* using a suite of bioassays, *Nanotoxicology* 8 (2014) 1-16.
- [8] M.A. Muflikhun, A.Y. Chua, G.N.C. Santos, Statistical design analysis of silver-titanium dioxide nanocomposite materials synthesized via horizontal vapor phase growth (HVPG), *Key Eng. Mater.* 735 (2017) 210-214.
- [9] M.K. Seery, R. George, P. Floris, S.C. Pillai, Silver doped titanium dioxide nanomaterials for enhanced visible light, photocatalysis 189 (2007) 258-263.

- [10] S.F. Chin, S.C. Pang, F. Emmanuel, I. Dom, Sol-gel synthesis of silver/titanium dioxide (Ag/TiO₂) core-shell nanowires for photocatalytic applications, *Mater. Lett.* 65 (2011) 2673-2675.
- [11] Z. Xiong, J. Ma, W.J. Ng, T.D. Waite, X.S. Zhao, Silver-modified mesoporous TiO₂ photocatalyst for water purification, *Water Res.* 45 (2011) 2095-2103.
- [12] M. Samiei, A. Farjami, S.M. Dizaj, F. Lotfipour, Nanoparticles for antimicrobial purposes in Endodontics: a systematic review of in vitro studies, *Mater. Sci. Eng. C* 58 (2016) 1269-1278.
- [13] M.V. Liga, E.L. Bryant, V.L. Colvin, Q. Li, Virus inactivation by silver doped titanium dioxide nanoparticles for drinking water treatment, *Water Res.* 45 (2011) 535-544.
- [14] K. Laohhasurayotin, S. Pookboonmee, Multifunctional properties of Ag/TiO₂ /bamboo charcoal composites: preparation and examination through several characterization methods, *Appl. Surf. Sci.* 282 (2013) 236-244.
- [15] C.F. Chau, S.H. Wu, G.C. Yen, The development of regulations for food nanotechnology, *Trends Food Sci. Technol.* 18 (2007) 269-280.
- [16] M. Lungu, Silver e titanium dioxide nanocomposites as effective antimicrobial and antibiofilm agents, *J. Nanopart. Res.* 16 (2014) 1-15.
- [17] F.C. Yang, K.H. Wu, J.W. Huang, D.N. Horng, C.F. Liang, M.K. Hu, Preparation and characterization of functional fabrics from bamboo charcoal/silver and titanium dioxide/silver composite powders and evaluation of their antibacterial efficacy, *Mater. Sci. Eng. C* 32 (2012) 1062-1067.
- [18] Skorb, E.V.; Antonouskaya, L.I.; Belyasova, N.A.; Shchukin, D.G.; Möhwald, H.; Sviridov, D.V. Antibacterial activity of thin-film photocatalysts based on metal-modified TiO₂ and TiO₂:In₂O₃ nanocomposite. *Appl. Catal. B* **2008**, 84, 94–99.
- [20] Liu, Y.; Zeng, X.K.; Hu, X.Y.; Hu, J.; Wang, Z.Y.; Yin, Y.C.; Sun, C.H.; Zhang, X.W. Two-dimensional Ag-C₃N₄/TiO₂ nanocomposites as vertical Z-scheme heterojunction for improved photocatalytic water disinfection. *Catal. Today* **2019**, 335, 243–251.
- [21] Sikora, P.; Cendrowski, K.; Markowska-Szczupak, A.; Horszczaruk, E.; Mijowska, E. The effects of silica/titania nanocomposite on the mechanical and bactericidal properties of cement mortars. *Constr. Build. Mater.* **2017**, 150, 738–746.
- [22] B. Subash, B. Krishnakumar, M. Swaminathan, and M. Shanthi, “Highly efficient, solar active, and reusable photocatalyst: Zr-loaded Ag–ZnO for reactive red 120 dye degradation with synergistic effect and dye-sensitized mechanism,” *Langmuir*, vol. 29, no. 3, pp. 939–949, 201

[23] Enrico traversa *et al*, Sol-Gel Processed TiO₂-Based Nano-Sized Powders for Use in Thick-Film Gas Sensors for Atmospheric Pollutant Monitoring, *Journal of Sol-Gel Science and Technology* 22, 167–179, 2001

[24] K. Kaviyarasu, N. Geetha, K. Kanimozhi, C. Maria Magdalane, S. Sivaranjani, A. Ayeshamariam, J. Kennedy, M. Maaza, In vitro cytotoxicity effect and antibacterial performance of human lung epithelial cells A549 activity of zinc oxide doped TiO₂ nanocrystals: investigation of bio-medical application by chemical method, *Mater. Sci. & Eng. C*, 74 (2017) 325-333.

[25] A. Angel Ezhilarasi, J. Judith Vijaya, K. Kaviyarasu, M. Maaza, A. Ayeshamariam, L. John Kennedy, Green synthesis of NiO nanoparticles using *Moringa oleifera* extract and their biomedical applications: Cytotoxicity effect of nanoparticles against HT-29 cancer cells, *J. Photochem. & Photobio. B: Bio.* 164 (2016) 352-360.

[26] K. Kaviyarasu, C.M. Magdalane, K. Anand, E. Manikandan, M. Maaza, Synthesis and characterization studies of MgO:CuO nanocrystals by wet-chemical method, *Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy* 142 (2015) 405-409.

[27] K. Kaviyarasu, P.A. Devarajan, A convenient route to synthesize hexagonal pillar shaped ZnO nanoneedles via CTAB surfactant, *Adv. Mater. Lett* 4 (2013) 582-585.

[28] C.M. Magdalane, K. Kaviyarasu, J.J. Vijaya, C. Jayakumar, M. Maaza, B Jeyaraj, Photocatalytic degradation effect of malachite green and catalytic hydrogenation by UV-illuminated CeO₂/CdO multilayered nanoplatelet arrays: Investigation of antifungal and antimicrobial activities, *Journal of Photochemistry and Photobiology B: Biology* 169 (2017) 110-123.

[29] K. Kaviyarasu, L. Kotsedi, Aline Simo, Xolile Fuku, Genene. T. Mola, J. Kennedy, M. Maaza, Photocatalytic activity of ZrO₂ doped lead dioxide nanocomposites: Investigation of structural and optical microscopy of RhB organic dye, *Applied Surface Science*, Available online 21 November 2016 - <https://doi.org/10.1016/j.apsusc.2016.11.149>,

[30] K. Kaviyarasu, K. Kanimozhi, N. Matinise, C.M. Magdalane, Genene. T. Mola, J. Kennedy, M. Maaza, Antiproliferative effects on human lung cell lines A549 activity of

cadmium selenide nanoparticles extracted from cytotoxic effects: Investigation of bio-electronic application, Materials Science and Engineering: C 76 (2017) 1012-1025.

[31] X. Fuku, K. Kaviyarasu, N. Matinise, M. Maaza, Punicalagin Green Functionalized Cu/Cu₂O/ZnO/CuO Nanocomposite for Potential Electrochemical Transducer and Catalyst, Nanoscale Research Letters 11 (1) (2016) 386.

[32] K. Kaviyarasu, P.P. Murmu, J. Kennedy, F.T. Thema, Douglas Letsholathebe, L. Kotsedi, M. Maaza, Structural, optical and magnetic investigation of Gd implanted CeO₂ nanocrystals, Nucl. Instr. Meth. B (2017), <http://dx.doi.org/10.1016/j.nimb.2017.02.055>.

[33] A. Chanderiya, G. A. N, A. Ratnesh Das, U. I. Hassan, S. K. Kashaw, S. Pandey, Recent Advances in Metal Nanoparticles for the Synthesis of N-Containing Heterocyclic Compound, Asian Journal of Chemistry, 33, 5, (2021), 949-955.

[34] S. Pandey, E. Fosso-Kankeu, M.J. Spiro, F. Waanders, N. Kumar, S.S. Ray, J. Kim, M. Kang, Equilibrium, kinetic, and thermodynamic studies of lead ion adsorption from mine wastewater onto MoS₂-clinoptilolite composite, Materials Today Chemistry, 18, (2020), 100376,

[35] S Pandey, C. De Klerk, J. Kim, M. Kang, E. Fosso-Kankeu, Eco Friendly Approach for Synthesis, Characterization and Biological Activities of Milk Protein Stabilized Silver Nanoparticles, Polymers, 12, (2020), 1418.