

Feasibility Study Toward Biogas Purification of H₂S Impurities

Using Wet and Dry Banana Leaves

Haryono Setiyo Huboyo^{1*}, Badrus Zaman¹, Bimastyaji Surya Ramadan¹, Agung Budi Prasetyo²,
Rahmatia Sarah Wahyudi¹

¹Environmental Engineering Department, Diponegoro University, INDONESIA

²Computer Engineering Department, Diponegoro University, INDONESIA

*Corresponding author:

E-mail: huboyo@lecturer.undip.ac.id, Tel: +62-24-76480678

ACCEPTED MANUSCRIPT

ABSTRACT

Biogas, an alternative technology that produces environmentally friendly fuels, usually contains impurities which may infer the performance of combustion. Hydrogen sulfide (H_2S) gas is one of the impurities in the biogas. This study's objective is to assess the removal of hydrogen sulfide using banana leaves. Dry and wet banana leaves were selected to remove pure H_2S gas using simple arranged equipment. Scanning Electron Microscopy (SEM) and Energy-Dispersive X-ray Spectroscopy (EDX) analysis was also performed to establish the effect of H_2S adsorption on the surface of banana leaves. The adsorption capacity was determined using the adsorption isotherm equation. Wet banana leaves have a higher H_2S gas adsorption efficiency than dry banana leaves. Based on the SEM image, the morphology of the banana leaves after adsorption shows that there is damage of the surface leaves morphology than before adsorption. The adsorption capacity of wet leaves is 1.25–1.29 times greater than those of dry leaves, based on the Freundlich and Langmuir isotherms. Based on this study, banana leaves have the potential to be used as an impurity remover for H_2S in biogas. Further research with real biogas stocks is needed to obtain their true efficiency.

Keywords: biogas, impurity, material, nature, removal

1. Introduction

Fossil fuels represent approximately 80% of the global primary energy consumption in 2023 (IEA, 2024). In 2020, oil, coal, and natural gas supplied 30%, 26%, and 23% of the total energy supply respectively worldwide (Fernandez et al., 2024). For this reason, massive development of renewable energy is indispensable. Renewable energy development actually has the advantage of reducing political dependence on energy imports (Adebayo et al., 2021) and reducing environmental impacts, because renewable energy does not emit carbon emissions into the environment. The use of renewable energy in the last three decades has, driven by political support, continued to grow, developing increasingly advanced technology, and decreasing the cost of producing renewable energy (Renné, 2022). Biomass energy consisting of agricultural waste, forest waste, human waste, and animal waste can be used to meet various energy needs (Malik et al., 2021). Biomass energy has advantages over other forms of renewable energy, due to its accessibility and large storage capacity (Ozturk et al., 2017). In relation to climate change mitigation, biomass energy has the advantage of being carbon neutral (Ni et al., 2006).

Biogas is an alternative technology that produces environmentally friendly fuels because it comes from biomass (Q. Wang et al., 2023), organic waste (Tumusiime et al., 2022), organic liquid waste (Nurjuwita et al., 2020), food waste (C. Zhang et al., 2022), leaves (Vargas-Soplín et al., 2022), and animal waste (Abdeshahian et al., 2016; Khalil et al., 2019). From anaerobic activity by methane bacteria, biogas is able to produce gases such as CH_4 , CO_2 , H_2S , and other gases. Typically biogas comprises of 50–75% methane (CH_4), 25–50% carbon dioxide (CO_2), 0–10% nitrogen (N_2), 0–3% hydrogen sulfide (H_2S), 0–1% hydrogen (H_2), and trace gases (Aghel et al., 2022). While biogas in animal manure consists of 53% CH_4 , 46% CO_2 , 1% O_2 , and 200 ppm sulfur (Eggemann et al., 2023). Other study investigates the production of biogas through the utilization of domestic waste or food waste in a biogas plant consisting of 42% methane, 45% carbon dioxide, 2.4% oxygen, and 156-193 ppm hydrogen sulfide (Catherine & Twizerimana, 2022).

From the gas content, there are several gas impurities such as CO₂ and H₂S which can interfere with the performance of biogas (Dupnock & Deshusses, 2020), especially related to combustion performance and SO₂ pollutant emission levels. In addition, the relatively high H₂S content in biogas can cause the corrosion of process equipment and have a negative impact on the environment, so these impurities must be removed by purification (Cristiano et al., 2020). Various methods of biogas purification have been carried out in several studies. These include water scrubbing (Noorain et al., 2019), physicochemical absorption (Liu et al., 2014; Maile et al., 2017), membrane separation (Zito et al., 2022), biotrickling filtration (Vikromvarasiri et al., 2017). Other methods that can also be used to separate H₂S from biogas are absorbent as a gas purifier (Surra et al., 2019). Because each of these purification techniques is unique, the best technology should be chosen by taking into account factors including investment, maintenance costs, operating circumstances, and purifying efficiency. As for discussion of which application of biogas will be used in local communities, it would be more appropriate to use the biosorption method, the ingredients required being easy to find in the local environment.

The concentration of hydrogen sulfide gas in biogas is relatively small (± 0.1 –2%) (Zhuo et al., 2022). High concentrations of this gas in biogas can cause corrosion in the combustion chamber (Latosov et al., 2017). In addition, this gas has an unpleasant odor (Omri et al., 2013), is toxic (Vovusha et al., 2019), and its combustion produces sulfur dioxide gas (Pompanon et al., 2022). It is a poisonous gas that, at high enough quantities (over 100 parts per million), can kill humans by poisoning their respiratory, endocrine, and central neurological systems (B. Zhang et al., 2022). Thus, there is an immediate need for sophisticated and effective H₂S removal technologies. Numerous efficient physical and chemical techniques, such as adsorption, catalytic combustion, catalytic oxidation, and neutralization, have been documented up to this point for the desulfurization of odorous waste gases. Actually, the process of H₂S gas removal has been carried out through several types of processes such as adsorption process (Fan et al., 2013; Feng et al., 2017; Sun et al., 2016; Balsamo et al., 2016; Cui et al., 2022; H. Zhang et al., 2021), absorption process (Y. Wang et al., 2019; Y. Wang et al., 2020;

Liu et al., 2021), membrane process (Atash Jameh et al., 2025; Jusoh et al., 2025) and biological process (Brito et al., 2025; Do Vale Borges et al., 2025). The use of cheap adsorbent materials is preferred with special considerations for the use of biogas purification. Additionally, this research develops inexpensive adsorbent materials using agricultural by-products.

A review of banana plants' possible applications has been completed recently. Several conventional adsorbents used to absorb pollutant gases and impurities have been investigated by many researchers. However, the use of banana plants as a commercial adsorbent in overcoming air pollution is not yet available (Sumiyati et al., 2019). Experiments carried out by Huboyo et al (2022) showed that the H₂S gas adsorption efficiency values of three banana components—leaves, stems, and peel—were 76.52%, 51.83%, and 6.44%, respectively (Huboyo et al., 2022). According to this study, banana leaves have a promising future as H₂S gas absorbers. The adsorption process is linked to some of the physicochemical properties of banana leaves as a biosorbent for gaseous contaminants. According to the findings of the SEM characterization, the banana leaf's morphology possesses a porous surface that, in certain investigations, may trap pollutants inside its stomata or pores. Lignin, cellulose, and cuticular wax are among the chemical properties of banana leaves that can be utilized to make gas adsorbents (Wahyudi et al., 2022).

Considering the study's findings, banana leaves potentially become adsorbent through their characteristics and efficiency parameter as adsorbent. Therefore, this study will continue the previous research, in which banana leaves were used as biosorbents from the H₂S gas adsorption process, and will differentiate between leaf conditions when wet and dry. Furthermore, it will examine feasibility of banana leaves to become a biogas purifier

2. Materials and methods

2.1. Tools and Materials

For sample weighing, an analytic balance (Mettler Toledo, Type ME204) was used; it was calibrated in September 2021. Pure H₂S gas (mixed with N₂) was introduced into a 50 L Tedlar bag with a special H₂S regulator. H₂S was introduced at a constant flow rate of 50 mL/min with a mass flow

controller (Aalborg, GFCS-015466) for ten different contact times (5, 10, 15, 20, 25, 30, 35, 40, 45, and 50 minutes). Details of the equipment (Figure 1) used can be seen in the previous experiment (Wahyudi et al., 2023). We use a UV-Vis spectrophotometer (Thermoscientific Genesys 10S) to analyze the H_2S concentration using methylene blue in accordance with the Indonesian National Standard (SNI) 19-7117.7-2005.

2.2. Preparation of Banana Leaves as Biosorbent

Banana leaves are prepared from local banana plants. Leaves that are mature enough are selected. In this study there are two types of absorbents, namely wet banana leaves and dry banana leaves. Some of the initial steps that were applied to both types of absorbents were washing them with distilled water and wiping them before cutting them to a size of around 1 mm x 1 mm. To prepare wet banana leaves as an absorbent, drying is carried out by leaving them at room temperature for 24 hours. With dry banana leaves, after cutting, oven drying is carried out at 110°C for two hours.

2.3. Experimental System and Procedures

Methylene blue spectrophotometry is the test method used in this study. As stated in the Indonesian National Standard 19-7117.7-2005, several steps are required, including the determination of the calibration curve, testing of test samples after the adsorption running process has been carried out, and concentration calculations.

Determination of the calibration curve is done by finding the factor (f) of sodium thiosulfate solution, determining the volume of the H_2S mother liquor, and making a calibration curve. The value of factor (f) is found by titrating the solution (25 mL KIO_3 + 100 mL distilled water + 2 gr KI + 10 mL HCl 1:10 in an Erlenmeyer flask) with the TiO solution until light yellow and adding 5 mL of starch indicator until the blue color has just disappeared; the volume of the penitar solution is then recorded and the TiO factor value was obtained. Then the volume of the H_2S main liquor was determined by the titration method, where sodium thiosulfate was used as the titrant, while the H_2S main liquor and the blank (distilled water) were used as the titrant. In making the calibration curve, using a

spectrophotometer at a wavelength of 670 nm, the four absorbance values obtained were then analyzed for the curve and the curve equation was also obtained.

Twenty milliliters of the sample solution were put into each measurement tube. 1 mL of FeCl₃, and 2 mL of p-aminodimethylaniline were added, then the sample was homogenized. After being homogenized once more, each tube was left for half an hour, after which it was diluted with distilled water to a 25 mL limit. At wavelength 670 nm, the absorbance of the measurement sample solution was measured, and a calibration curve was used to calculate the amount of H₂S gas present. Next, the concentration of the absorbent solution that had gone through the adsorption process was calculated according to the Indonesian National Standard 19-7117.7-2005.




Figure 1. Simple Arranged Equipment

2.4. Data Analysis

Analysis of the data obtained to obtain the value of the adsorption capacity of H₂S on wet and dry banana leaves using the Freundlich and Langmuir adsorption isotherm theory. Freundlich's concept derives the following equation:

$$\frac{X_m}{m} = k \cdot C^{1/n}$$

$$\text{Log} \left(\frac{X_m}{m} \right) = \text{Log} k + \frac{1}{n} \cdot \text{Log} C$$

where

X_m = adsorbed weight

m = adsorbent weight

C = substance concentration

Then k and n are adsorption constants whose value depends on the type of adsorbent and the adsorption temperature. When a curve of $\log (X_m / m)$ against $\log C$ is made, a linear equation will be obtained with an intercept of $\log k$ and a slope of $1/n$, so that the values of k and n can be calculated, while Langmuir's concept derives the following equation:

$$\frac{X_m}{m} = \frac{a \cdot C}{1 + b \cdot C}$$
$$m \cdot \frac{C}{X_m} = \frac{1}{a} + \left(\frac{b}{a}\right) \cdot C$$

By making a curve of $m \cdot C / X_m$ to C , a linear equation will be obtained with an intercept of $1/a$ and a slope (b/a) , so that the values of a and b can be calculated, from the size of the values of a and b indicating the adsorption capacity.

2.5. SEM-EDX Analysis

The size, shape, and surface characteristics of the tested adsorbent particles were examined using SEM both before and after adsorption for each sample type. SEM EDX analysis was performed using Phenom ProX (The Netherlands). The components in the adsorbents, particularly S (sulfur), were quantified using the EDX.

3. Results and Discussion

3.1. H₂S Removal Performance

Table 1 contains data regarding the concentration of sulfuric acid pollutant gas (H₂S) on various types of adsorbents (wet leaves and dry leaves) and variations in contact time carried out by triplication.

Table 1. H₂S Concentration after Adsorption Process (ppm)

Adsorbent Type	Contact Time (minutes)									
	5	10	15	20	25	30	35	40	45	50
Wet Leaves	134.10	208.41	217.99	217.99	220.02	226.11	229.89	232.50	237.43	257.17
	44.99	178.51	184.90	188.96	207.83	210.15	211.31	218.28	222.05	224.66
	58.34	162.84	197.67	217.12	220.89	238.89	243.24	267.33	280.68	280.68
Average	79.14	183.25	200.18	208.02	216.25	225.05	228.15	239.37	246.72	254.17

Stdev	48.06	23.15	16.69	16.51	7.30	14.40	16.04	25.24	30.40	28.13
	185.77	237.72	245.85	249.34	253.98	255.43	274.30	277.49	285.62	310.29
Dry Leaves	116.40	171.84	172.42	190.70	195.35	207.25	208.70	215.95	229.02	252.53
	193.31	205.80	227.86	231.05	239.18	239.76	242.37	248.75	254.85	258.62
Average	165.16	205.12	215.37	223.70	229.50	234.14	241.79	247.40	256.49	273.81
Stdev	42.40	32.95	38.28	30.00	30.49	24.58	32.80	30.79	28.34	31.74

In Figure 1, the variation in contact time is linear with the resulting concentration value. In the adsorption process with banana leaf adsorbent, the concentration of H_2S gas increased with contact time when the lowest concentration was 44.99 mg/L and the highest was 310.29 mg/L. The difference in concentration of the 10 variations looks relatively stable with a contact time interval of five minutes. For the first 5 minutes of the experiment, there was a fairly intense adsorption process at the beginning so that there was high fluctuation between samples, both in wet and dry leaves. Further experiments are suggested to be able to provide more detailed time at the beginning of the adsorption process.

Contact time between the adsorbent and the adsorbate that is too long can cause the adsorbent conditions to become saturated and release of the adsorbate (Petrović et al., 2023). As can be seen in Figure 2, from the test results, the concentration of H_2S gas continued to rise with increasing contact time, so it can be concluded that the banana leaf adsorbent reached saturation level in a short time.




Figure 2. Graph of H_2S Concentration (Average)

The adsorption efficiency of H_2S gas of two adsorbents is significantly different. Average wet banana leaves have the highest adsorption efficiency of H_2S gas of 73.62% while dry banana leaves have an adsorption efficiency of 44.95%. Wet banana leaves have a higher H_2S gas adsorption efficiency compare to dry banan leaves because wet banana leaves have natural fiber structure and higher water content than dry leaves so that the adsorption process can occur more intensely due to the high solubility of H_2S gas in water which is facilitated by its natural fiber structure. . Fibers owned by banana leaves include cellulose, hemicellulose, and lignin (Wahyudi et al., 2022).

Adsorption efficiency is affected by contact time. According to the results of the study, five minutes is the best adsorption efficiency at 0 – 10 minutes experiments because H_2S gas adsorption occurs to a maximum level. However, the optimum adsorption conditions need to be studied further to see the optimal conditions by taking into account the factors of the amount of material used, adsorption time and acceptable removal rate. After the five-minute contact time, the adsorption efficiency value decreased due to the contact time between the adsorbent and the adsorbate, which was too long and caused the adsorbent to become saturated and the adsorbate to be released. Past the optimum conditions, the adsorbent no longer works.

Figure 3 and Figure 4 demonstrate the efficiency of H_2S gas removal on wet and dry banana leaves. The gas removal efficiency of each adsorbent after 5 minutes is not significant from each treatment due to the lack of difference between two types of adsorbents in percentage of removal.




Figure 3. Graph of the Efficiency of H₂S Gas Removal on Wet Banana Leaves






Figure 4. Graph of the Efficiency of H₂S Gas Removal on Dry Banana Leaves

3.2. SEM-EDX Characterization of Banana Leaves

SEM results of wet and dry banana leaves before and after adsorption are shown in Figure 5 and Figure 6. Figure 5 is a SEM image of a wet banana leaf before and after adsorption




(A)




(B)

Figure 5. SEM Result of Wet Leaves. (A) Before Adsorption (B) After Adsorption



(A)



(B)

Figure 6. SEM Result of Dry Leaves (A) Before Adsorption (B) After Adsorption

As seen in the figure, before adsorption the stomata were visible and there were few materials attached around the stomata. However, after adsorption the stomata are covered with materials sticking around them. This increasing amount of material arises due to damage of the morphology of the leaf surface. The same is seen in Figure 6, which is a SEM image of dried banana leaves before and after adsorption in which the morphology of the banana leaves after adsorption demonstrates damage to the morphology of the leaf surface compare to that before adsorption. This morphology damage may be due to the H_2S adsorption process that occurs in the two leaves as demonstrated in research conducted by Gao (2021) explaining that stomata can trap air pollution (Gao et al., 2021). In addition, a study from Zheng (2022) explains that the wax structure on leaves can block pollution (Zheng et al., 2022).

Based on EDX analysis (Table 2 dan Table 3), there was an increase in sulfur levels in leaves after the adsorption process, particularly from sulfur elements. The use of wet banana leaves increased the sulfur content in the leaves by about 1.6 times as compared to dry banana leaves that increased by only 1.04 times. The increase in the S element in this study was lower than previous study (Huboyo et al., 2022) which reached 20 times, but it was comparable to latest study (Wahyudi et al., 2023) which was around 1-1.6 times using various types of wet banana leaves. This demonstrates that banana leaves have potential as H₂S gas adsorbers.

Table 2. EDX Results on Wet Banana Leaves

Element Symbol	Wet Banana Leaves							
	Before Adsorption		After Exp 1		After Exp 2		After Exp 3	
	Atomic Conc.	Weight Conc.	Atomic Conc.	Weight Conc.	Atomic Conc.	Weight Conc.	Atomic Conc.	Weight Conc.
C	69.50	62.93	74.19	66.88	76.02	67.78	66.67	58.94
O	14.16	17.08	23.25	25.31	17.36	20.19	21.94	25.49
S	0.04	0.11	0.09	0.18	0.23	0.54	0.07	0.17
Si	0.09	0.19	3.24	5.89	0.30	0.62	1.68	3.45
P	0.04	0.09	0.08	0.19	0.17	0.39	0.10	0.23
N	15.33	16.24	20.21	18.40	9.52	9.13	8.34	8.48
K	0.56	1.63	0.90	2.37	1.49	4.06	0.98	2.81

Table 3. EDX Results on Dry Banana Leaves

Element Symbol	Dry Banana Leaves							
	Before Adsorption		After Exp 1		After Exp 2		After Exp 3	
	Atomic Conc.	Weight Conc.	Atomic Conc.	Weight Conc.	Atomic Conc.	Weight Conc.	Atomic Conc.	Weight Conc.
C	58.99	53.09	77.39	69.51	81.60	75.58	62.24	55.36
O	30.78	31.88	10.07	12.10	22.89	26.20	16.82	19.86
S	0.04	0.08	0.06	0.13	0.11	0.25	0.05	0.11
Si	0.02	0.05	1.44	2.91	0.22	0.47	0.02	0.05
P	0.09	0.19	0.05	0.12	0.15	0.32	0.11	0.25
N	15.23	13.77	10.19	10.79	23.14	21.09	19.04	19.78
K	2.31	5.70	0.25	0.73	0.81	2.31	1.24	3.56

3.3. Adsorption Isotherm

The adsorption capacity (the amount of H₂S gas adsorbed in each unit weight of the adsorbent) is expressed in mg/g adsorbent. The adsorption capacity is determined using the adsorption isotherm equation. The adsorption isotherm models used are the Freundlich adsorption isotherm and the Langmuir adsorption isotherm. Figures 7, 8, 9 and 10 show the Freundlich and Langmuir isotherm equations for wet and dry leaves.




Figure 7. Graph of Wet Banana Leaves Freundlich Adsorption Isotherm




Figure 8. Graph of Wet Banana Leaves Langmuir Adsorption Isotherm




Figure 9. Graph of Dry Banana Leaves Freundlich Adsorption Isotherm




Figure 10. Graph of Dry Banana Leaves Langmuir Adsorption Isotherm

Based on the calculation of the adsorption model for each isotherm, depending upon the type of wet banana leaf adsorbent, the regression coefficient on the Freundlich isotherm is 0.8426 with an adsorption capacity of 5.8182 mg/g adsorbent. The best regression coefficient for dry banana leaf adsorbent comes from the calculation of the Freundlich isotherm with a value of 0.8713 and an adsorption capacity of 4.6562 mg/g adsorbent. Table 4 is a summary of the adsorption capacity.

Table 4. Adsorption Capacity

Adsorbent Type (Banana Leaves)	Freundlich Isotherm		Langmuir Isotherm	
	R	Capacity (mg/g)	R	Capacity (mg/g)
Wet Leaves	0.843	5.818	0.509	5.335
Dry Leaves	0.871	4.656	0.578	4.148

The results of this adsorption capacity are slightly lower than previous studies (Wahyudi et al., 2023) for the same type of banana leaf, around 7.6 mg/g. These two studies indicate that the adsorption capacity of banana leaves is influenced by their water content and type.

3.4. Implication of H₂S Reduction in Biogas Purification

Biogas purification reduces the corrosive impact on the machinery by eliminating impurities like hydrogen sulfide. Additionally, the procedure removes pollutants' detrimental impacts on the environment and human health. Moreover the elimination of impurities raises the fraction of methane that is useable energy, improving the fuel's energy density. (Das et al., 2022).

Adsorption is one method of removing hydrogen sulfide both during and after digestion. In this study, it was found that both wet and dry banana leaves can be used as adsorbents in the H₂S gas adsorption process. Based on literature, livestock waste has a H₂S gas content reaching a concentration of 200 ppm (Eggemann et al., 2023). If carried out using the banana leaf adsorption process, the lowest output concentration of H₂S is expected to be 52.76 ppm. If tried with lower efficiency i.e. 44.95%, the H₂S output concentration reaches 110.1 ppm.

The use of wet banana leaves can reduce banana leaf waste, especially after the banana harvest. Not all banana leaves have economic value, i.e., are marketable. The use of wet banana leaves (not through drying treatment) will facilitate the practicality of making adsorbents. Fortunately, banana plants are usually found in rural areas where the potential for biogas is higher, especially from livestock waste, so there is an effortless supply chain in terms of providing adsorbents. On the other hand, it is still necessary to study the use of this used adsorbent. For example, if it is becoming fertilizer after going through the composting process, it should consider that the S content in it increases.

This study used pure H₂S gas as its adsorbate, hence ideal adsorption conditions for H₂S gas may occur. It's still unknown regarding the adsorption competition with other hydrophillic gases such as CO₂ and NH₃. These two impurity gases are present in sufficient amount in biogas

From this study, further research can be conducted regarding the effect of banana leaves adsorbent on real biogas purification, especially on adsorption competition for impurity gases.

4. Conclusion

Wet and dry banana leaves can be used as adsorbents for H₂S gas adsorbate. The adsorption efficiency of H₂S gas of two adsorbents is significantly different in that average wet banana leaves have the highest adsorption efficiency of H₂S gas of 73.62% and dry banana leaves have 44.95%. Based on SEM images, there are proven changes to the morphology of the banana leaf surface due to the adsorption process. Adsorption capacity was higher for wet leaves than that of dry leaves based on Freundlich and Langmuir isotherms. Based on this study, banana leaves have the potential to be used as an impurity remover for H₂S in biogas. From this research it appears to be feasible to use the banana leaf adsorbent as a biogas purifier particularly for H₂S gas. Further research with real biogas experimentation is necessary.

Acknowledgements

This research was funded by the Ministry of Education, Culture, Research and Technology of the Republic of Indonesia, contract number: 225–101/UN7.6.1/PP/2021. Our laboratory technicians (Mr. Andi, Mr. Andri) in Diponegoro University are highly acknowledged for assisting laboratory experiments.

Author contributions

Haryono S Huboyo: Conceptualization, Methodology, Writing Review Editing, Funding Acquisition. **Badrus Zaman:** Data curation, Writing review, Supervision. **Bimastyaji Surya Ramadan:** Investigation, Lab Analysis, Writing- Original draft preparation. **Rahmatia Sarah:** Investigation, Lab Analysis. **Agung Budi Prasetijo:** Assisting set up device and visualization.

Data availability

All data supporting the findings of this study are available upon request

Consent for publication

Consent to publish was obtained from all authors.

Declaration of competing interest

The authors declare that they have no competing financial interests or personal relationships that could have appeared to influence the work reported in this paper.

References

- Abdeshahian, P., Lim, J. S., Ho, W. S., Hashim, H., & Lee, C. T. (2016). Potential of biogas production from farm animal waste in Malaysia. *Renewable and Sustainable Energy Reviews*, 60, 714–723. <https://doi.org/10.1016/j.rser.2016.01.117>
- Adebayo, T. S., Udemba, E. N., Ahmed, Z., & Kirikkaleli, D. (2021). Determinants of consumption-based carbon emissions in Chile: an application of non-linear ARDL. *Environmental Science and Pollution Research*, 28(32), 43908–43922. <https://doi.org/10.1007/s11356-021-13830-9>
- Aghel, B., Behaein, S., & Alobiad, F. (2022). CO₂ capture from biogas by biomass-based adsorbents: A review. *Fuel*, 328(March), 125276. <https://doi.org/10.1016/j.fuel.2022.125276>
- Atash Jameh, A., Mohammadi, T., & Bakhtiari, O. (2025). A novel methanol medium modification of ZIF-8 nanoparticles and their incorporation into the Pebax 1074 membranes for simultaneous CO₂ and H₂S removal from natural gas. *Chemical Engineering Research and Design*, 218, 682–696. <https://doi.org/https://doi.org/10.1016/j.cherd.2025.05.020>
- Balsamo, M., Cimino, S., de Falco, G., Erto, A., & Lisi, L. (2016). ZnO-CuO supported on activated carbon for H₂S removal at room temperature. *Chemical Engineering Journal*, 304, 399–407. <https://doi.org/https://doi.org/10.1016/j.cej.2016.06.085>
- Brito, J., Frade-González, C., Almenglo, F., González-Cortés, J. J., Valle, A., Durán-Ruiz, M. C., & Ramírez, M. (2025). Anoxic desulfurization of biogas rich in hydrogen sulfide through feedback control using biotrickling filters: Operational limits and multi-omics analysis. *Bioresource Technology*, 428, 132439. <https://doi.org/https://doi.org/10.1016/j.biortech.2025.132439>
- Catherine, C., & Twizerimana, M. (2022). Biogas production from thermochemically pretreated sweet potato root waste. *Heliyon*, 8(9), e10376. <https://doi.org/10.1016/j.heliyon.2022.e10376>
- Cristiano, D. M., de A. Mohedano, R., Nadaleti, W. C., de Castilhos Junior, A. B., Lourenço, V. A.,

- Gonçalves, D. F. H., & Filho, P. B. (2020). H₂S adsorption on nanostructured iron oxide at room temperature for biogas purification: Application of renewable energy. *Renewable Energy*, 154, 151–160. <https://doi.org/10.1016/j.renene.2020.02.054>
- Cui, S., Zhao, Y., Liu, Y., & Pan, J. (2022). Preparation of copper-based biochar adsorbent with outstanding H₂S adsorption capacity and study on H₂S removal. *Journal of the Energy Institute*, 105, 481–490. <https://doi.org/10.1016/j.joei.2022.11.004>
- Das, J., Ravishankar, H., & Lens, P. N. L. (2022). Biological biogas purification: Recent developments, challenges and future prospects. *Journal of Environmental Management*, 304(September 2021), 114198. <https://doi.org/10.1016/j.jenvman.2021.114198>
- Do Vale Borges, A., Zamariolli Damianovic, M. H. R., & Torre, R. M. (2025). Assessment of aerobic-anoxic biotrickling filtration for the desulfurization of high-strength H₂S streams from sugarcane vinasse fermentation. *Journal of Hazardous Materials*, 489, 137696. <https://doi.org/10.1016/j.jhazmat.2025.137696>
- Dupnock, T. L., & Deshusses, M. A. (2020). Biological Co-treatment of H₂S and reduction of CO₂ to methane in an anoxic biological trickling filter upgrading biogas. *Chemosphere*, 256, 127078. <https://doi.org/10.1016/j.chemosphere.2020.127078>
- Eggemann, L., Rau, F., & Stolten, D. (2023). The ecological potential of manure utilisation in small-scale biogas plants. *Applied Energy*, 331(June 2022), 120445. <https://doi.org/10.1016/j.apenergy.2022.120445>
- Fan, H.-L., Sun, T., Zhao, Y.-P., Shangguan, J., & Lin, J.-Y. (2013). Three-Dimensionally Ordered Macroporous Iron Oxide for Removal of H₂S at Medium Temperatures. *Environmental Science & Technology*, 47(9), 4859–4865. <https://doi.org/10.1021/es304791b>
- Feng, Y., Wen, J., Hu, Y., Wu, B., Wu, M., & Mi, J. (2017). Evaluation of the cycling performance of a sorbent for H₂S removal and simulation of desulfurization-regeneration processes. *Chemical Engineering Journal*, 326, 1255–1265. <https://doi.org/10.1016/j.cej.2017.05.098>

- Fernandez, M. I., Go, Y. I., Wong, D. M. L., & Fröh, W. G. (2024). Review of challenges and key enablers in energy systems towards net zero target: Renewables, storage, buildings, & grid technologies. *Heliyon*, 10(23), e40691. <https://doi.org/10.1016/j.heliyon.2024.e40691>
- Gao, P. P., Xue, P. Y., Dong, J. W., Zhang, X. M., Sun, H. X., Geng, L. P., Luo, S. X., Zhao, J. J., & Liu, W. J. (2021). Contribution of PM_{2.5}-Pb in atmospheric fallout to Pb accumulation in Chinese cabbage leaves via stomata. *Journal of Hazardous Materials*, 407(September 2020), 124356. <https://doi.org/10.1016/j.jhazmat.2020.124356>
- Huboyo, H. S., Zaman, B., Ramadan, B. S., & Prinaningrum, A. D. (2022). Promising Adsorption of Sulfidic Acid Gases Using Wet Banana Plant Adsorbent (*Musa* spp.). *Journal of Engineering and Technological Sciences*, 54(1). <https://doi.org/10.5614/j.eng.technol.sci.2022.54.1.10>
- IEA. (2024). *World Energy Outlook*. IEA. <https://iea.blob.core.windows.net/assets/a5ba91c9-a41c-420c-b42e-1d3e9b96a215/WorldEnergyOutlook2024.pdf>
- Jusoh, N., Adibah Tengku Hassan, T. N., Suhaimi, N. H., & Mubashir, M. (2025). Hydrogen sulfide removal from biogas: An overview of technologies emphasizing membrane separation. *Separation and Purification Technology*, 373, 133466. <https://doi.org/10.1016/j.seppur.2025.133466>
- Khalil, M., Berawi, M. A., Heryanto, R., & Rizalie, A. (2019). Waste to energy technology: The potential of sustainable biogas production from animal waste in Indonesia. *Renewable and Sustainable Energy Reviews*, 105(July 2018), 323–331. <https://doi.org/10.1016/j.rser.2019.02.011>
- Latosov, E., Loorits, M., Maaten, B., Volkova, A., & Soosaar, S. (2017). Corrosive effects of H₂S and NH₃ on natural gas piping systems manufactured of carbon steel. *Energy Procedia*, 128, 316–323. <https://doi.org/10.1016/j.egypro.2017.08.319>
- Liu, Y., Li, H., Wei, G., Zhang, H., Li, X., & Jia, Y. (2014). Mass transfer performance of CO₂ absorption by alkanolamine aqueous solution for biogas purification. *Separation and Purification Technology*, 133, 476–483. <https://doi.org/10.1016/j.seppur.2014.07.028>

- Liu, Y., Shi, S., & Wang, Y. (2021). Removal of pollutants from gas streams using Fenton (-like)-based oxidation systems: A review. *Journal of Hazardous Materials*, 416, 125927. <https://doi.org/https://doi.org/10.1016/j.jhazmat.2021.125927>
- Maile, O. I., Muzenda, E., & Tesfagiorgis, H. (2017). Chemical Absorption of Carbon Dioxide in Biogas Purification. *Procedia Manufacturing*, 7, 639–646. <https://doi.org/10.1016/j.promfg.2016.12.095>
- Malik, P., Awasthi, M., & Sinha, S. (2021). Biomass-based gaseous fuel for hybrid renewable energy systems: An overview and future research opportunities. *International Journal of Energy Research*, 45(3), 3464–3494. <https://doi.org/https://doi.org/10.1002/er.6061>
- Ni, M., Leung, D. Y. C., Leung, M. K. H., & Sumathy, K. (2006). An overview of hydrogen production from biomass. *Fuel Processing Technology*, 87(5), 461–472. <https://doi.org/https://doi.org/10.1016/j.fuproc.2005.11.003>
- Noorain, R., Kindaichi, T., Ozaki, N., Aoi, Y., & Ohashi, A. (2019). Biogas purification performance of new water scrubber packed with sponge carriers. *Journal of Cleaner Production*, 214, 103–111. <https://doi.org/10.1016/j.jclepro.2018.12.209>
- Nurjuwita, W., Sasongko, A., Hartanto, T. J., & Purwanto, M. (2020). Potential and characterization biogas from tofu liquid waste with addition cow dung and effective microorganisms 4 as biocatalyst. *Materials Today: Proceedings*, 46, 1908–1912. <https://doi.org/10.1016/j.matpr.2021.02.025>
- Omri, I., Aouidi, F., Bouallagui, H., Godon, J. J., & Hamdi, M. (2013). Performance study of biofilter developed to treat H₂S from wastewater odour. *Saudi Journal of Biological Sciences*, 20(2), 169–176. <https://doi.org/10.1016/j.sjbs.2013.01.005>
- Ozturk, M., Saba, N., Altay, V., Iqbal, R., Hakeem, K. R., Jawaid, M., & Ibrahim, F. H. (2017). Biomass and bioenergy: An overview of the development potential in Turkey and Malaysia. *Renewable and Sustainable Energy Reviews*, 79(March), 1285–1302. <https://doi.org/10.1016/j.rser.2017.05.111>

- Petrović, R., Lazarević, S., Janković-Častvan, I., Matic, T., Milivojević, M., Milošević, D., & Veljović. (2023). Removal of trivalent chromium from aqueous solutions by natural clays: Valorization of saturated adsorbents as raw materials in ceramic manufacturing. *Applied Clay Science*, 231(July 2022). <https://doi.org/10.1016/j.clay.2022.106747>
- Pompanon, F., Fouvry, S., & Alquier, O. (2022). Influence of the relative humidity and H₂S - SO₂ polluted air on the fretting wear behavior of silver-plated electrical contacts. *Wear*, 508–509(July), 204455. <https://doi.org/10.1016/j.wear.2022.204455>
- Renné, D. S. (2022). Progress, opportunities and challenges of achieving net-zero emissions and 100% renewables. *Solar Compass*, 1(March), 100007. <https://doi.org/10.1016/j.solcom.2022.100007>
- Sumiyati, S., Huboyo, H. S., & Ramadan, B. S. (2019). Potential Use of Banana Plant (*Musa* spp.) as Bio-sorbent Materials for Controlling Gaseous Pollutants. *E3S Web of Conferences*, 125(2019), 1–6. <https://doi.org/10.1051/e3sconf/201912503015>
- Sun, Y., Zhang, J. P., Wen, C., & Zhang, L. (2016). An enhanced approach for biochar preparation using fluidized bed and its application for H₂S removal. *Chemical Engineering and Processing: Process Intensification*, 104, 1–12. <https://doi.org/10.1016/j.cep.2016.02.006>
- Surra, E., Costa Nogueira, M., Bernardo, M., Lapa, N., Esteves, I., & Fonseca, I. (2019). New adsorbents from maize cob wastes and anaerobic digestate for H₂S removal from biogas. *Waste Management*, 94, 136–145. <https://doi.org/10.1016/j.wasman.2019.05.048>
- Tumusiime, E., Kirabira, J. B., & Musinguzi, W. B. (2022). Optimization of substrate mixing ratios for wet anaerobic digestion of selected organic waste streams for productive biogas systems. *Energy Reports*, 8, 10409–10417. <https://doi.org/10.1016/j.egyr.2022.08.189>
- Vargas-Soplín, A. de J., Prochnow, A., Herrmann, C., Tscheuschner, B., & Kreidenweis, U. (2022). The potential for biogas production from autumn tree leaves to supply energy and reduce greenhouse gas emissions – A case study from the city of Berlin. *Resources, Conservation and Recycling*, 187(June). <https://doi.org/10.1016/j.resconrec.2022.106598>

- Vikromvarasiri, N., Champreda, V., Boonyawanich, S., & Pisutpaisal, N. (2017). Hydrogen sulfide removal from biogas by biotrickling filter inoculated with *Halothiobacillus neapolitanus*. *International Journal of Hydrogen Energy*, 42(29), 18425–18433. <https://doi.org/10.1016/j.ijhydene.2017.05.020>
- Vovusha, H., Hussain, T., Sajjad, M., Lee, H., Karton, A., Ahuja, R., & Schwingenschlögl, U. (2019). Sensitivity enhancement of stanene towards toxic SO₂ and H₂S. *Applied Surface Science*, 495(June), 143622. <https://doi.org/10.1016/j.apsusc.2019.143622>
- Wahyudi, R. S., Huboyo, H. S., Sutrisno, E., & Zaman, B. (2022). Characteristics of Banana Leaves as Gaseous Biosorbent. *IOP Conference Series: Earth and Environmental Science*, 1098(1). <https://doi.org/10.1088/1755-1315/1098/1/012063>
- Wahyudi, R. S., Huboyo, H. S., & Zaman, B. (2023). Removal of Hydrogen Sulfide Gas Pollutants with Various Wet Banana Leaf Types. *Water, Air, and Soil Pollution*, 234(5), 1–13. <https://doi.org/10.1007/s11270-023-06301-z>
- Wang, Q., Xia, C., Alagumalai, K., Thanh Nhi Le, T., Yuan, Y., Khademi, T., Berkani, M., & Lu, H. (2023). Biogas generation from biomass as a cleaner alternative towards a circular bioeconomy: Artificial intelligence, challenges, and future insights. *Fuel*, 333(P2), 126456. <https://doi.org/10.1016/j.fuel.2022.126456>
- Wang, Y., Wang, Y., & Liu, Y. (2020). Removal of gaseous hydrogen sulfide using ultraviolet/Oxone-induced oxidation scrubbing system. *Chemical Engineering Journal*, 393, 124740. <https://doi.org/https://doi.org/10.1016/j.cej.2020.124740>
- Wang, Y., Wang, Z., Pan, J., & Liu, Y. (2019). Removal of gaseous hydrogen sulfide using Fenton reagent in a spraying reactor. *Fuel*, 239, 70–75. <https://doi.org/https://doi.org/10.1016/j.fuel.2018.10.143>
- Zhang, B., Wang, Y., Zhu, H., Huang, S., Zhang, J., Wu, X., Li, B., & Xiao, X. (2022). Evaluation of H₂S gas removal by a biotrickling filter: Effect of oxygen dose on the performance and microbial communities. *Process Safety and Environmental Protection*, 166(March), 30–40.

<https://doi.org/10.1016/j.psep.2022.07.054>

- Zhang, C., Sun, Y., Cao, T., Wang, W., Huo, S., & Liu, Z. H. (2022). Influence of organic load on biogas production and response of microbial community in anaerobic digestion of food waste. *International Journal of Hydrogen Energy*, 47(77), 32849–32860. <https://doi.org/10.1016/j.ijhydene.2022.07.187>
- Zhang, H., Wang, J., Liu, T., Zhang, M., Hao, L., Phoutthavong, T., & Liang, P. (2021). Cu-Zn oxides nanoparticles supported on SBA-15 zeolite as a novel adsorbent for simultaneous removal of H₂S and Hg⁰ in natural gas. *Chemical Engineering Journal*, 426, 131286. <https://doi.org/https://doi.org/10.1016/j.cej.2021.131286>
- Zheng, W., Ma, Y., Tigabu, M., Yi, Z., Guo, Y., Lin, H., Huang, Z., & Guo, F. (2022). Capture of fire smoke particles by leaves of *Cunninghamia lanceolata* and *Schima superba*, and importance of leaf characteristics. *Science of the Total Environment*, 841(June), 156772. <https://doi.org/10.1016/j.scitotenv.2022.156772>
- Zhuo, Y., Yang, P., Zhou, M., Peng, D., & Han, Y. (2022). Low H₂S content biogas biodesulfurization from high solid sludge anaerobic digestion using limited external aeration biotrickling filter: Effect of gas-liquid pattern on oxygen utilization performance. *Journal of Environmental Management*, 314(February), 115084. <https://doi.org/10.1016/j.jenvman.2022.115084>
- Zito, P. F., Brunetti, A., & Barbieri, G. (2022). Renewable biomethane production from biogas upgrading via membrane separation: Experimental analysis and multistep configuration design. *Renewable Energy*, 200(July), 777–787. <https://doi.org/10.1016/j.renene.2022.09.124>